

Technical Data

产品说明

Overview
PULSE™ 230 is a high-heat PC/ABS resin delivering optimized performance for automotive interior component applications in the Asia Region

- Benefits
- Easy flow, reduced scrap, and shorter cycle times, while enabling thin wall part design for mass reduction.
 - High low-temperature impact
 - High Heat resistance for demanding automotive interior components
 - High quality appearance solution: consistent natural white color with color concentrates or Trinseo Color Masterbatch Technology
 - Low odor & VOC to meet all global Automotive OEM specification

- Applications:
- Mid (floor)consoles
 - Instrument Panel components
 - Door panel trim
 - Pillars
 - Storage / load floors / glove box

总览

材料状态	• 已商用：当前有效		
资料 ¹	• Technical Datasheet		
搜索 UL 黄卡	• Trinseo • PULSE™		
供货地区	• 亚太地区		
特性	• 良好的加工性能 • 流动性高	• 耐低温冲击 • 热稳定性，良好	• 韧性良好
用途	• 汽车领域的应用	• 汽车内部零件	• 汽车仪表板
形式	• 粒子		
加工方法	• 注射成型		

物理性能	额定值	单位制	测试方法
密度	1.13 g/cm³		ISO 1183
熔流率 (熔体流动速率) (260°C/5.0 kg)	18 g/10 min		ISO 1133
机械性能	额定值	单位制	测试方法
拉伸模量	2300 MPa		ISO 527-1/1
拉伸应力 (屈服)	54.0 MPa		ISO 527-2/50
拉伸应变			ISO 527-2/50
屈服	4.0 %		
断裂	100 %		
冲击性能	额定值	单位制	测试方法
简支梁缺口冲击强度			ISO 179/1eA
-30°C	40 kJ/m²		
23°C	50 kJ/m²		
热性能	额定值	单位制	测试方法
载荷下热变形温度 (1.8 MPa, 未退火)	108 °C		ISO 75-2/A
维卡软化温度	130 °C		ISO 306/B50



注射	额定值 单位制
干燥温度	100 °C
干燥时间	4.0 hr
加工（熔体）温度	255 到 290 °C
模具温度	60 到 80 °C

备注

¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。

² 一般属性：这些不能被视为规格。

