

Technical Data

产品说明

Overview

PULSE™ GX50 ECO is a PC/ABS blend which contains 30% recycling content according to ISO14021. A further contribution to a favorable eco balance is provided by the low density of this grade. A high quality and consistency level like for the standard PULSE™ GX50 is achieved for this resin. This grade is only available in standard black.

Benefits

- Contains 30% recycling content according to ISO14021
- Low density
- Easy processability, heat performance and Low temperature impact equivalent to PULSE™ GX50

Applications

- Automotive interior and exterior parts

总览

材料状态	• 已商用：当前有效
资料 ¹	• Technical Datasheet
搜索 UL 黄卡	• Trinseo • PULSE™
供货地区	• 欧洲
回收含量	• 是, 30%
形式	• 粒子
加工方法	• 注射成型

物理性能

	额定值 单位制	测试方法
密度	1.09 g/cm³	ISO 1183
熔流率 (熔体流动速率) (260°C/5.0 kg)	12 g/10 min	ISO 1133
Spiral Flow ³	50.0 cm	
收缩率	0.40 到 0.70 %	ISO 294-4
VOC Content	15.0 µg/g	VDA 277

机械性能

	额定值 单位制	测试方法
拉伸模量	2000 MPa	ISO 527-1/1
拉伸应力 (屈服)	44.0 MPa	ISO 527-2/50
拉伸应变 (断裂)	80 %	ISO 527-2/50

冲击性能

	额定值 单位制	测试方法
简支梁缺口冲击强度		ISO 179/1eA
-30°C	50 kJ/m²	
23°C	60 kJ/m²	

热性能

	额定值 单位制	测试方法
载荷下热变形温度 (1.8 MPa, 未退火)	90.0 °C	ISO 75-2/A
维卡软化温度	107 °C	ISO 306/B50
线形热膨胀系数 - 流动 (-30 到 80°C)	7.5E-5 到 8.0E-5 cm/cm/°C	ISO 11359-2



注射	额定值 单位制
干燥温度	100 °C
干燥时间	4.0 hr
加工（熔体）温度	255 到 280 °C
模具温度	60 到 80 °C

备注

- ¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
- ² 一般属性：这些不能被视为规格。
- ³ 熔体温度: 260°C, 注塑压力: 1.80E+3 bar

