

Technical Data

产品说明

Overview
PULSE™ GX50 is an easy flow, medium-heat, low gloss and low density PC/ABS resin delivering optimized performance for automotive interior component applications.

- Benefits
- Low gloss allowing paint-less visible applications
 - Low density driving to lighter and cost optimized parts
 - Easy flow, reduced scrap, and faster cycle times, while enabling thin wall part design for mass reduction
 - High-impact strength even at low temperature
 - Heat resistance optimized for the majority of automotive interior components
 - Consistent natural white color produces high quality part appearance when used with color concentrates (self coloring) or Trinseo Color Masterbatch Technology
 - Low odor & VOC to meet all global Automotive OEM specifications

- Applications
- Mid (floor)consoles
 - Lower Instrument Panel components
 - Door panel trim
 - Pillars
 - Storage / load floors / glove box

总览

材料状态	• 已商用：当前有效		
资料 ¹	• Technical Datasheet		
搜索 UL 黄卡	• Trinseo • PULSE™		
供货地区	• 北美洲	• 欧洲	• 亚太地区
特性	• 低光泽 • 低密度 • 高抗撞击性	• 流动性高 • 耐低温冲击 • 耐热性，良好	• 韧性良好
用途	• 汽车领域的应用	• 汽车内部零件	
形式	• 粒子		
加工方法	• 注射成型		

物理性能	额定值 单位制	测试方法
密度	1.09 g/cm³	ISO 1183
表观密度	0.63 g/cm³	ISO 60
熔流率 (熔体流动速率) (260°C/5.0 kg)	12 g/10 min	ISO 1133
Spiral Flow ³	50.0 cm	
收缩率	0.40 到 0.70 %	ISO 294-4
VOC Content	15.0 µg/g	VDA 277
机械性能	额定值 单位制	测试方法
拉伸模量	2000 MPa	ISO 527-1/1
拉伸应力 (屈服)	44.0 MPa	ISO 527-2/50
拉伸应变 (断裂)	80 %	ISO 527-2/50



冲击性能	额定值 单位制	测试方法
简支梁缺口冲击强度		ISO 179/1eA
-30°C	50 kJ/m²	
23°C	60 kJ/m²	
热性能	额定值 单位制	测试方法
载荷下热变形温度 (1.8 MPa, 未退火)	90.0 °C	ISO 75-2/A
维卡软化温度	107 °C	ISO 306/B50
线形热膨胀系数 - 流动 (-30 到 80°C)	7.5E-5 到 8.0E-5 cm/cm/°C	ISO 11359-2
注射	额定值 单位制	
干燥温度	100 °C	
干燥时间	4.0 hr	
加工 (熔体) 温度	255 到 280 °C	
模具温度	60 到 80 °C	

备注

- ¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
- ² 一般属性：这些不能被视为规格。
- ³ 熔体温度: 260°C, 注塑压力: 1.80E+3 bar