

PULSE™ GX70 ECO

PC/ABS Engineering Resin

Trinseo

PROSPECTOR®

www.ulprospector.com

Technical Data

产品说明

Overview

PULSE™ GX70 ECO is a PC/ABS blend which contains 50% recycling content according to ISO14021. A high quality and consistency level like for the standard PULSE™ GX70 is achieved for this resin. It combines consistent and easy processability with good low temperature impact resistance. The heat resistance is tailor made to resist most automotive interior and exterior component requirements. The grade is only available in standard black.

Benefits

- Contains 50% recycling content according to ISO14021
- Easy processability, heat performance and low temperature impact equivalent to PULSE™ GX70

Applications:

- Automotive interior and exterior parts

总览

材料状态	• 已商用：当前有效
资料 ¹	• Technical Datasheet
搜索 UL 黄卡	• Trinseo • PULSE™
供货地区	• 欧洲
回收含量	• 是, 50%
形式	• 粒子
加工方法	• 注射成型

物理性能	额定值 单位制	测试方法
密度	1.11 g/cm³	ISO 1183
熔速率 (熔体流动速率) (260°C/5.0 kg)	16 g/10 min	ISO 1133
Spiral Flow ³	47.0 cm	
收缩率	0.40 到 0.70 %	ISO 294-4
VOC Content	12.0 µg/g	VDA 277

机械性能	额定值 单位制	测试方法
拉伸模量	2150 MPa	ISO 527-1/1
拉伸应力 (屈服)	49.0 MPa	ISO 527-2/50
拉伸应变 (断裂)	> 80 %	ISO 527-2/50

冲击性能	额定值 单位制	测试方法
简支梁缺口冲击强度		ISO 179/1eA
-30°C	50 kJ/m²	
23°C	55 kJ/m²	

热性能	额定值 单位制	测试方法
载荷下热变形温度 (1.8 MPa, 未退火)	98.0 °C	ISO 75-2/A
维卡软化温度	117 °C	ISO 306/B50
线形热膨胀系数 - 流动 (-30 到 80°C)	7.5E-5 到 8.0E-5 cm/cm/°C	ISO 11359-2

注射	额定值 单位制
干燥温度	100 °C
干燥时间	4.0 hr
加工 (熔体) 温度	255 到 280 °C
模具温度	60 到 80 °C



备注

- ¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
- ² 一般属性：这些不能被视为规格。
- ³ 熔体温度: 260°C, 注塑压力: 1.80E+3 bar

