

Technical Data

产品说明

Overview
PULSE™ XT9215 is an easy flow, high-heat, low density mineral filled PC/ABS resin delivering optimized performance for automotive exterior component applications requiring low CLTE for a better dimensional stability.

- Benefits
- Very low CLTE for an improved dimensional stability (smaller gaps) and a better fit and finish for optimal quality
 - High ductility and easy flow for more design freedom (larger/longer parts, optimized wall thickness)and better economics (improved cycle time)
 - Significant density advantage (up to 10% compared to a PC/PET) for lighter parts and optimized costs
 - Faster cycle times for a better process cost control
 - High gloss for painted applications with enhanced paint adhesion

- Applications
- Spoilers
 - Exterior trims
 - Roof bows
 - Roof rails

总览

材料状态	• 已商用：当前有效		
资料 ¹	• Technical Datasheet		
搜索 UL 黄卡	• Trinseo • PULSE™		
供货地区	• 北美洲	• 欧洲	• 亚太地区
填料/增强材料	• 矿物填料, 15% 填料按重量		
特性	• 低 CLTE • 高光	• 可喷涂的 • 良好的流动性	• 耐热性，中等
用途	• 汽车领域的应用	• 汽车外部零件	• 汽车外部装饰
形式	• 粒子		
加工方法	• 注射成型		

物理性能	额定值	单位制	测试方法
密度	1.25	g/cm³	ISO 1183
表观密度	0.63	g/cm³	ISO 60
熔速率 (熔体流动速率) (260°C/5.0 kg)	24	g/10 min	ISO 1133
Spiral Flow ^{3, 4}	44.0	cm	
收缩率	0.20 到 0.60	%	ISO 294-4
机械性能	额定值	单位制	测试方法
拉伸模量	4200	MPa	ISO 527-1/1
拉伸应力 (屈服)	53.0	MPa	ISO 527-2/5
拉伸应变 (断裂)	15	%	ISO 527-2/5
冲击性能	额定值	单位制	测试方法
简支梁缺口冲击强度 (23°C)	10	kJ/m²	ISO 179/1eA

热性能	额定值 单位制	测试方法
载荷下热变形温度 (1.8 MPa, 未退火)	108 °C	ISO 75-2/A
维卡软化温度	132 °C	ISO 306/B50
线形热膨胀系数 - 流动 (-30 到 80°C)	3.5E-5 到 4.0E-5 cm/cm/°C	ISO 11359-2

注射	额定值 单位制
干燥温度	120 °C
干燥时间	5.5 hr
加工 (熔体) 温度	255 到 280 °C
模具温度	60 到 80 °C

备注

- ¹ 通过这些链接您能够访问供应商资料。我们尽量保证及时更新资料；不过您可以从供应商处了解最新资料。
- ² 一般属性：这些不能被视为规格。
- ³ 熔体温度: 260°C, 注塑压力: 1.80E+3 bar
- ⁴ 2 mm thickness

