# 产品物性表　Technical Data

## POLYWING B1HG8

- 主要特征：PA6，40%玻纤增强，高耐热，注塑级。
- Product Description：PA6, 40%GF, High heat resistance, Injection Molding.

| 性能 Properties | 测试条件 Test Condition | 典型值 Typical Value | 国际单位 Unit | 测试标准 Test Standard |
|---|---|---|---|---|
| **机械性能 Mechanical** | | | | |
| 拉伸强度 Tensile Strength | 5mm/min | 180 | MPa | ISO 527 |
| 断裂伸长率 Tensile Strain at Break | 5mm/min | 3.5 | % | ISO 527 |
| 弯曲模量 Flexural Strength | 2mm/min | 10000 | MPa | ISO 178 |
| 弯曲强度 Flexural Modulus | 2mm/min | 265 | MPa | ISO 178 |
| 悬臂梁缺口冲击 Izod Notched Impact Strength | 4mm | 17 | $kJ/m^2$ | ISO 180 |
| **物理性能 Physical** | | | | |
| 比重 Density | 23℃ | 1.47 | g/cm3 | ISO 1183-1 |
| 收缩率 Molding Shrinkage | - | 0.3~0.6 | % | ISO 294-4 |
| **阻燃性能 Flammability** | | | | |
| 阻燃等级 Flame Rating | 0.8mm | HB | - | UL 94 |
| **热性能 Thermal** | | | | |
| 热变形温度 Temperature of Deflection Under Load | 1.8MPa | 210 | ℃ | ISO 75 |

## 典型加工条件 Typical Processing Conditions

| | 典型范围<br>Range (Optimum) | 单位<br>unit |
|---|---|---|
| 预干燥温度 Pre-dry Temperature | 100~120 | ℃ |
| 预干燥时间 Pre-dry Time | 4~6 | hrs |
| 熔体温度 Melt Temperature | 250~285 | ℃ |
| 料筒后段温度 Rear Temperature | 220~260 | ℃ |
| 料筒中段温度 Middle Temperature | 240~270 | ℃ |
| 料筒前段温度 Front Temperature | 250~280 | ℃ |
| 模温 Mold Temperature | 60~90 | ℃ |

*数据为实验典型值，只作为客户使用的参考，不作为质保承诺。

不同的颜色性能可能会不同。

*These are typical values of the product's properties, and these values alone do not represent a sufficient basis for any part design and are not intended for use in not the permit of quality assurance.

The listed values are maybe different for pigmented material.