

Akulon® S223-KG7

PA66-GF35

Glass Reinforced, Heat Stabilized, for E&E applications

Print Date: 2019-01-24

Properties	Typical Data	Unit	Test Method
Rheological properties			
	dry / cond		
Molding shrinkage (parallel)	0.2 / *	%	ISO 294-4
Molding shrinkage (normal)	1 / *	%	ISO 294-4
Mechanical properties			
	dry / cond		
Tensile modulus	11500 / 7550	MPa	ISO 527-1/-2
Stress at break	210 / 140	MPa	ISO 527-1/-2
Strain at break	3.5 / 5.8	%	ISO 527-1/-2
Flexural modulus	9400 / -	MPa	ISO 178
Flexural strength	270 / -	MPa	ISO 178
Charpy impact strength (+23°C)	89 / 95	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	74 / 74	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	14 / 18	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	11 / 11	kJ/m ²	ISO 179/1eA
Thermal properties			
	dry / cond		
Melting temperature (10°C/min)	260 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	247 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	260 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.6 / *	E-4/°C	ISO 11359-1/-2
Other properties			
	dry / cond		
Water absorption	5.5 / *	%	Sim. to ISO 62

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. This document replaces all previous versions relating to this subject.

Copyright © DSM 2018. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.


DSM

BRIGHT SCIENCE. BRIGHTER LIVING.

Property Data

Akulon[®] S223-KG7

Print Date: 2019-01-24

Properties	Typical Data	Unit	Test Method
Humidity absorption	1.5 / *	%	Sim. to ISO 62
Density	1410 / -	kg/m ³	ISO 1183

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. This document replaces all previous versions relating to this subject.

Copyright © DSM 2018. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.