

Arnite® LT TV4 261

PBT-GF30

Laser Transparent Black, Laser Weldable

Print Date: 2022-06-24

Properties	Typical Data	Unit	Test Method
Rheological properties			
	Value		
Melt volume-flow rate	17	cm ³ /10min	ISO 1133
Temperature	275	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (normal)	1.35	%	ISO 294-4
Molding shrinkage (parallel)	0.35	%	ISO 294-4
Mechanical properties			
	Value		
Tensile modulus	10200	MPa	ISO 527-1/-2
Stress at break	135	MPa	ISO 527-1/-2
Strain at break	2.5	%	ISO 527-1/-2
Charpy impact strength (+23°C)	45	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	37	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	8.7	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	7.9	kJ/m ²	ISO 179/1eA
Thermal properties			
	Value		
Melting temperature (10°C/min)	223	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	205	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75-1/-2
Electrical properties			
	Value		
Electric strength	37	kV/mm	IEC 60243-1
Comparative tracking index	375	V	IEC 60112

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl®, UDea™ and Xytron™ are trademarks of DSM.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. This document replaces all previous versions relating to this subject.

Copyright © DSM 2022. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.

Property Data (Provisional)

Arnite[®] LT TV4 261

Print Date: 2022-06-24

Properties	Typical Data	Unit	Test Method
Other properties	Value		
Density	1540	kg/m ³	ISO 1183

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl®, UDea™ and Xytron™ are trademarks of DSM.

Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. This document replaces all previous versions relating to this subject.

Copyright © DSM 2022. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.

**DSM**

BRIGHT SCIENCE. BRIGHTER LIVING.