

Arnitel® ECO L406

TPC

>50% Renewable Content, UV Stabilized

Print Date: 2023-08-09

Sustainability

Bio-based – 14C measurable

Properties	Typical Data	Unit	Test Method
Rheological properties	Value		
Melt volume-flow rate	45	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
Molding shrinkage (parallel)	1.2	%	ISO 294-4
Molding shrinkage (normal)	1.2	%	ISO 294-4
Molding shrinkage [parallel]	1.2	%	Sim. to ISO 294-4
Molding shrinkage [normal]	1.2	%	Sim. to ISO 294-4
Mechanical properties	Value		
Shore D Hardness (3s)	34	-	ISO 868
Tensile modulus	40	MPa	ISO 527-1/-2
Stress at break	9	MPa	ISO 527-1/-2
Nominal strain at break	200	%	ISO 527-1/-2
Stress at 5% strain	2.7	MPa	ISO 527-1/-2
Stress at 10% strain	4.5	MPa	ISO 527-1/-2
Stress at 50% strain	7.7	MPa	ISO 527-1/-2
Stress at 100% strain	8.3	MPa	ISO 527-1/-2
Tear strength	75	kN/m	ISO 34-1; Method B
Compression Set under constant strain at 70 °C	47	%	ISO 815

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl®, UDea™ and Xytron™ are trademarks of Envalior. Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. This document replaces all previous versions relating to this subject.

Copyright © Envalior 2023. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.


DSM

BRIGHT SCIENCE. BRIGHTER LIVING.

Property Data (Provisional)

Arnitel[®] ECO L406

Print Date: 2023-08-09

Properties	Typical Data	Unit	Test Method
Thermal properties			
Melting temperature (10°C/min)	158	°C	ISO 11357-1/-3
Vicat softening temperature (50°C/h 10N)	90	°C	ISO 306
Electrical properties			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	>1E15	Ohm	IEC 62631-3-2
Electric strength	20	kV/mm	IEC 60243-1
Other properties			
Density	1100	kg/m ³	ISO 1183
Humidity absorption	0.04	%	Sim. to ISO 62
Biobased content (in polymer)	52	% (Bio C/Total C)	ASTM D6866-12 Method B

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl®, UDea™ and Xytron™ are trademarks of Envalior. Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied. Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect. Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. This document replaces all previous versions relating to this subject. Copyright © Envalior 2023. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

