

Arnitel® ECO L400

TPC

>50% Renewable Content

Print Date: 2017-02-06

Properties	Typical Data	Unit	Test Method
Rheological properties			
Melt volume-flow rate	45	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133

Mechanical properties

Shore D Hardness (3s)	34	-	ISO 868
Tensile modulus	50	MPa	ISO 527-1/-2
Stress at break	12	MPa	ISO 527-1/-2
Nominal strain at break	300	%	ISO 527-1/-2
Stress at 5% strain	2.7	MPa	ISO 527-1/-2
Stress at 10% strain	4.5	MPa	ISO 527-1/-2
Stress at 50% strain	7.7	MPa	ISO 527-1/-2
Stress at 100% strain	8.3	MPa	ISO 527-1/-2

Thermal properties

Melting temperature (10°C/min)	158	°C	ISO 11357-1/-3
Vicat softening temperature (50°C/h 10N)	90	°C	ISO 306
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10

Electrical properties

Volume resistivity	>1E13	Ohm*m	IEC 60093
Surface resistivity	>1E15	Ohm	IEC 60093

Akulon®, Arnitel®, Arnitel®, EcoPaXX®, ForTil®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.
 All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.
 Typical values are indicative only and are not to be construed as being binding specifications.
 DSM reserves the right, at its sole discretion, to modify, discontinue or terminate all or a portion of the above statement, at any time and without advance notice. Any such modification, discontinuation or termination will take effect as from the date of that modification, discontinuation or termination.
 Copyright © DSM 2017. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.

Properties	Typical Data	Unit	Test Method
Electric strength	20	kV/mm	IEC 60243-1
Other properties			
Density	1100	kg/m ³	ISO 1183
Humidity absorption	0.04	%	Sim. to ISO 62
Biobased content	52	% (Bio C/Total C)	ASTM D6866-12 Method B

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications.

DSM reserves the right, at its sole discretion, to modify, discontinue or terminate all or a portion of the above statement, at any time and without advance notice. Any such modification, discontinuation or termination will take effect as from the date of that modification, discontinuation or termination.

Copyright © DSM 2017. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.

