

Arnitel® ECO L550

TPC

34% Renewable Content, Injection Molding

Print Date: 2019-05-14

Properties	Typical Data	Unit	Test Method
Rheological properties			
	Value		
Melt volume-flow rate	44	cm ³ /10min	ISO 1133
Temperature	230	°C	ISO 1133
Load	2.16	kg	ISO 1133
Mechanical properties			
	Value		
Shore D Hardness (3s)	55	-	ISO 868
Tensile modulus	165	MPa	ISO 527-1/-2
Stress at break	37	MPa	ISO 527-1/-2
Nominal strain at break	600	%	ISO 527-1/-2
Stress at 5% strain	8.2	MPa	ISO 527-1/-2
Stress at 10% strain	12.3	MPa	ISO 527-1/-2
Stress at 50% strain	14.7	MPa	ISO 527-1/-2
Stress at 100% strain	13.9	MPa	ISO 527-1/-2
Izod notched impact strength (+23°C)	N	kJ/m ²	ISO 180/1A
Izod notched impact strength (-30°C)	4.2	kJ/m ²	ISO 180/1A
Thermal properties			
	Value		
Melting temperature (10°C/min)	196	°C	ISO 11357-1/-3
Vicat softening temperature (50°C/h 50N)	59	°C	ISO 306
Vicat softening temperature (50°C/h 10N)	156	°C	ISO 306
Burning Behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. This document replaces all previous versions relating to this subject.

Copyright © DSM 2018. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.


DSM

BRIGHT SCIENCE. BRIGHTER LIVING.

Arnitel[®] ECO L550

Print Date: 2019-05-14

Properties	Typical Data	Unit	Test Method
Electrical properties		Value	
Volume resistivity	>1E13	Ohm*m	IEC 60093
Electric strength	20	kV/mm	IEC 60243-1
Other properties		Value	
Density	1170	kg/m ³	ISO 1183
Humidity absorption	0.03	%	Sim. to ISO 62
Biobased content	34	% (Bio C/Total C)	ASTM D6866-12 Method B

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. This document replaces all previous versions relating to this subject.

Copyright © DSM 2018. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.

