

Technical datasheet

GENESTAR™ G1300A-M31T BLACK (Laser Transparent)

GENESTAR™ is a brand name of heat resistant polyamide developed by Kuraray Co., Ltd. G1300A-M31T grade in that family is a 30% GF reinforced PA9T resin for injection molding provided as pellets. This grade is black and laser transparent which is suitable for laser welding.

The main features are:

- Performance at high temperature
- Low water absorption and retention of its initial properties
- Dimensional stability
- Laser transparency

This grade is suitable for

- Parts in harsh chemical and thermal environments

	Value*	Unit	Standard
Glass-fiber content	30	%	
Physical properties			
Specific gravity	1.36	-	ISO 1183
Water absorption (23° C, 24h)	0.19	%	ISO 62
Mold shrinkage - parallel	0.3	%	ISO 294-4
Mold shrinkage - normal	0.9	%	ISO 294-4
Mechanical properties			
Tensile strength	175	MPa	ISO 527
Tensile elongation at break	2.5	%	ISO 527
Flexural strength	245	MPa	ISO 178
Flexural modulus	8.8	GPa	ISO 178
Charpy impact strength - notched	10	kJ m ⁻²	ISO 179/1eA
Thermal properties			
Melting point	300	° C	ISO 11357-3
Glass transition temperature	125	° C	-
DTUL (1.80 MPa)	270	° C	ISO 75Af

* all values are measured in dry condition as molded

To the best of our knowledge, the information contained herein is accurate. It is the sole responsibility of the customer to determine whether the product is appropriate and suitable for customer's specific use. Specific end use may require approval by appropriate regulatory agencies. Kuraray makes no warranties, express or implied, regarding products on any information contained herein. Kuraray disclaims any liability for infringement of any patent due to customer's use of any Kuraray products in combination with other materials or in any process.

Contact Information

Japan

Kuraray Co., Ltd.
Tokiwabashi Tower., 2-6-4,
Otemachi, Chiyoda-ku, Tokyo, Japan,
100-0004
Tel + 81 03 6701 2125
Email: genestar.jp@kuraray.com

China

Kuraray Trading (Shanghai) Co., Ltd.
Unit 2106, 2 Grand Gateway, 3
Hongqiao Road,
Xu Hui District, Shanghai, 200030,
China
Tel +86 21 6407 9182
Email: genestar.cn@kuraray.com

Europe

EVAL Europe N.V. (Kuraray)
Haven 1087, Keetberglaan 1B
B-9120 Beveren Belgium
Tel +32 3 250 9766
Email: genestar.eu@kuraray.com

Korea

Kuraray Trading Co., Ltd.
4F Twin City Namsan, 366 Hangang-
daero,
Yongsan-gu, Seoul, 04323, Korea
+82 2 732 5637
Email: genestar.kr@kuraray.com

North Americas

Kuraray America, Inc.
39555 Orchard Hill Place, Suite 362
Novi, MI 48375
Tel +1 800 423 9762
Email: genestar.us@kuraray.com

Asia Pacific

Kuraray Asia Pacific Pte. Ltd.
250 North Bridge Road, #10-01/02
Raffles City Tower, Singapore 179101
Tel +65 6337 0116
Email: genestar.sg@kuraray.com

South Americas

Kuraray South America Ltda.
Av. Paulista, 1636 – Condomínio
Paulista Corporate, sala 405 – Bela
Vista, CEP 01310-200 – São Paulo –
SP – Brasil
Tel +55 11 2615 3531
Email: genestar.sa@kuraray.com

India

Kuraray India Private Limited
Prius Platinum, 2nd floor B wing, Rear
side, D3 district centre, Saket New
Delhi-110017, India
Tel +91 11 4090 4400
Email: genestar.in@kuraray.com