

Technical datasheet

GENESTAR™ G1300H-FO2

GENESTAR™ is a brand name of heat resistant polyamide developed by Kuraray Co., Ltd. G1300H-FO2 is a standard reinforced injection molding grade for E&E applications provided as pellets.

The main features are:

- Mechanical strength
- Processability
- Dimensional stability

This grade is suitable for

- FPC connectors
- Board-to-board and wire-to-board connectors

(Condition: 23°C)

	Value*	Unit	Standard
Glass-fiber content	30	%	
Physical properties			
Specific gravity	1.37	g cm ⁻³	ISO 1183
Water absorption (23°C, 24h)	0.19	%	ISO 62
Mechanical properties			
Tensile strength	150	MPa	ISO 527
Tensile elongation at break	1.9	%	ISO 527
Tensile modulus	9.5	GPa	ISO 527
Flexural strength	214	MPa	ISO 178
Flexural modulus	9.0	GPa	ISO 178
Weld line strength	40	MPa	Kuraray method based on ISO527
Charpy impact strength - notched	11.2	kJ m ⁻²	ISO 179/1eA
Thermal properties			
DTUL (1.8 MPa)	285	°C	ISO 75Af
Melting point	306	°C	ISO 11357-3
Glass transition temperature	125	°C	-
Molding properties			
Mold shrinkage – MD	0.3	%	ISO 294-4
Mold shrinkage – TD	1.0	%	ISO 294-4
Bar-flow length at 0.5 mm	53	mm	750 kgf, 320°C
Flammability			
Flame rating	HB	(0.8mm)	UL94
GWFI (t = 0.75, 1.5, 3.0 mm)	-	°C	IEC60695-2 10~13
GWIT (t = 0.75, 1.5, 3.0 mm)	-	°C	IEC60695-2 10~13

	Value*	Unit	Standard
Electrical properties			
Dielectric strength	28	kV/mm	IEC 60243-1
Tracking resistance (CTI)	0	PLC-class	UL746A
Dielectric loss tangent (1 GHz)	0.009		ASTM D2520
Dielectric loss tangent (10 GHz)	-		ASTM D2520

* all values are measured in dry condition as molded

To the best of our knowledge, the information contained herein is accurate. It is the sole responsibility of the customer to determine whether the product is appropriate and suitable for customer's specific use. Specific end use may require approval by appropriate regulatory agencies. Kuraray makes no warranties, express or implied, regarding products on any information contained herein. Kuraray disclaims any liability for infringement of any patent due to customer's use of any Kuraray products in combination with other materials or in any process.

Contact Information

Japan

Kuraray Co., Ltd.
Tokiwabashi Tower, 2-6-4
Otemachi, Chiyoda-ku, Tokyo, Japan,
100-0004
Tel + 81 03 6701 1000
Email: genestar.jp@kuraray.com

Europe

EVAL Europe N.V. (Kuraray)
Haven 1087, Keetberglaan 1B
B-9120 Beveren Belgium
Tel +32 3 250 9766
Email: genestar.eu@kuraray.com

North Americas

Kuraray America, Inc.
39555 Orchard Hill Place, Suite 362
Novi, MI 48375
Tel +1 800 423 9762
Email: genestar.us@kuraray.com

South Americas

Kuraray South America Ltda.
Av. Paulista, 1636 – Condomínio
Paulista Corporate, sala 405 – Bela
Vista, CEP 01310-200 – São Paulo –
SP – Brasil
Tel +55 11 2615 3531
Email: genestar.sa@kuraray.com

China

Kuraray Trading (Shanghai) Co., Ltd.
Unit 2106, 2 Grand Gateway, 3
Hongqiao Road,
Xu Hui District, Shanghai, 200030,
China
Tel +86 21 6407 9182
Email: genestar.cn@kuraray.com

Korea

Kuraray Trading Co., Ltd
11F Press Center, 124 Sejong-daero
Jung-gu, Seoul, 04520, KOREA
Tel +82 2 732 5637
Email: genestar.kr@kuraray.com

Asia Pacific

Kuraray Asia Pacific Pte. Ltd.
1 North Buona Vista Link, #12-10/11
Elementum
Singapore 139691
Email: genestar.sg@kuraray.com

India

Kuraray India Private Limited
World Trade Tower, Unit No. 1620, 16th
Floor, WTT Tower-B,
Plot No. C-1, Sector 16, Noida 201301
Uttar Pradesh, India
Tel +91 120 6923800
Email: genestar.in@kuraray.com