

产品物性表 Technical Data

POLYWING 3026

- ✧ 主要特征：PC/ABS 合金，无卤阻燃，注塑级。
- ✧ Product Description: PC/ABS Blend, Halogen Free Flame Retardant, Injection Molding.

性能 Properties	测试条件 Test Condition	典型值 Typical Value	国际单位 Unit	测试标准 Test Standard
------------------	------------------------	----------------------	--------------	-----------------------

机械性能 Mechanical

拉伸强度 Tensile Strength	50mm/min	55	MPa	ASTM D638
断裂伸长率 Tensile Strain at Break	50mm/min	>50	%	ASTM D638
弯曲模量 Flexural Strength	5mm/min	2500	MPa	ASTM D790
弯曲强度 Flexural Modulus	5mm/min	90	MPa	ASTM D790
悬臂梁缺口冲击 Izod Notched Impact Strength	3.18mm	550	J/m	ASTM D256

物理性能 Physical

比重 Density	23℃	1.18	g/cm³	ASTM D792
熔指 Melt Flow Index	260℃, 2.16kg	12	g/10min	ASTM D1238
收缩率 Molding Shrinkage	-	0.5-0.7	%	ASTM D955

阻燃性能 Flammability

阻燃等级 Flame Rating	1.5mm	V0	-	UL 94
-------------------	-------	----	---	-------

热性能 Thermal

热变形温度 Temperature of Deflection Under Load	1.8MPa	90	℃	ASTM D648
---	--------	----	---	-----------

典型加工条件 Typical Processing Conditions

	典型范围 Range (Optimum)	单位 unit
预干燥温度 Pre-dry Temperature	80	°C
预干燥时间 Pre-dry Time	4-6	hrs
熔体温度 Melt Temperature	220-240	°C
料筒后段温度 Rear Temperature	240-260	°C
料筒中段温度 Middle Temperature	245-265	°C
料筒前段温度 Front Temperature	250-270	°C
模温 Mold Temperature	60-90	°C

*数据为实验典型值，只作为客户使用的参考，不作为质保承诺。
不同的颜色性能可能会不同。
*These are typical values of the product’s properties, and these values alone do not represent a sufficient basis for any part design and are not intended for use in not the permit of quality assurance.
The listed values are maybe different for pigmented material.

安全及处理注意事项 Safety & Handling Considerations

急救措施

若吸入熔融树脂逸出之气体，将患者移至通风处，立即送医。若接触到熔胶，以大量（肥皂）水冲洗患部及衣物，立即送医。若接触到塑胶粒或塑胶粉末，以大量清水至少冲洗 15 分钟，若有不适，立即送医。若接触到高温熔融树脂逸出之气体，以大量清水至少冲洗 15 分钟，若有不适，立即送医。不慎吞食请催吐，以清水漱口，若有不适，立即送医。

FIRST AID MEASURES

Once inhaling of evaporated gas when the resin is melted, move subject to open space and seed medical advice immediately. Once contact with pellets or powder, flush with clean water for 15 min. Once contact with molten resin, flush with suds for 15 min and seed medical advice immediately. Seek medical advice immediately if any discomfortableness remains. Once swallowing accidentally, induce vomiting and rinse mouth with clean water. Seek medical advice if necessary.

安全处置与储存方法

处置操作处所须严禁烟火，做好整理整顿以避免粉尘累积。为防止尘爆，空气输送管路，袋滤器及储槽须加装静电消除装置，并确实接地。袋滤器之滤材采导电性材质。储存存放于阴凉处所，避免直射阳光，雨淋及急速之温差。储存处严禁烟火。

HANDLING AND STORAGE

Prohibit open fire and concentration of dust or powder in processing site and warehouse. To avoid dust explosion resulting from the existence of powder, electrostatics eliminators and grounding should be equipped to air transferring pipes, bag filters and hoppers. Additionally, use electrically conductive filters for bag filters. Store the goods in a cool and dry place. Protect from direct sunlight, rain and violent temperature fluctuation. Fire is inhibited around storage area