

产品物性表 Technical Data

POLYWING B1HG6

- ✧ 主要特征：PA6，30%玻纤增强，高耐热，注塑级。
- ✧ Product Description: PA6, 30%GF, High heat resistance, Injection Molding.

性能 Properties	测试条件 Test Condition	典型值 Typical Value	国际单位 Unit	测试标准 Test Standard
------------------	------------------------	----------------------	--------------	-----------------------

机械性能 Mechanical				
拉伸强度 Tensile Strength	5mm/min	170	MPa	ISO 527
断裂伸长率 Tensile Strain at Break	5mm/min	3.5	%	ISO 527
弯曲模量 Flexural Strength	2mm/min	7800	MPa	ISO 178
弯曲强度 Flexural Modulus	2mm/min	250	MPa	ISO 178
悬臂梁缺口冲击 Izod Notched Impact Strength	4mm	14	kJ/m ²	ISO 180
物理性能 Physical				
比重 Density	23℃	1.37	g/cm3	ISO 1183-1
收缩率 Molding Shrinkage	-	0.4~0.8	%	ISO 294-4
阻燃性能 Flammability				
阻燃等级 Flame Rating	0.8mm	HB	-	UL 94
热性能 Thermal				
热变形温度 Temperature of Deflection Under Load	1.8MPa	210	℃	ISO 75

典型加工条件 Typical Processing Conditions

	典型范围 Range (Optimum)	单位 unit
预干燥温度 Pre-dry Temperature	100~120	℃
预干燥时间 Pre-dry Time	4~6	hrs
熔体温度 Melt Temperature	250~285	℃
料筒后段温度 Rear Temperature	220~260	℃
料筒中段温度 Middle Temperature	240~270	℃
料筒前段温度 Front Temperature	250~280	℃
模温 Mold Temperature	60~90	℃

*数据为实验典型值，只作为客户使用的参考，不作为质保承诺。

不同的颜色性能可能会不同。

*These are typical values of the product's properties, and these values alone do not represent a sufficient basis for any part design and are not intended for use in not the permit of quality assurance.

The listed values are maybe different for pigmented material.