

LNP™ THERMOCOMP™ COMPOUND D151

REGION ASIA

DESCRIPTION

LNP* Thermocomp* D151 (experimental grade name as EXTC8274) is a compound based on Polycarbonate resin containing Glass Fiber, Flame Retardant. Added features of this material include: High modulus, good surface, good flatness, good ductility, Non-Brominated & Non-Chlorinated Flame Retardant.

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	83	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	3.6	%	ASTM D 638
Tensile Modulus, 5 mm/min	4400	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	131	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	4070	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	82	MPa	ISO 527
Tensile Strain, break, 5 mm/min	3.6	%	ISO 527
Tensile Modulus, 1 mm/min	4430	MPa	ISO 527
Flexural Stress, break, 2 mm/min	133	MPa	ISO 178
Flexural Modulus, 2 mm/min	4010	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	705	J/m	ASTM D 4812
Izod Impact, notched, 23°C	140	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	22	J	ASTM D 3763
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	13	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	50	kJ/m ²	ISO 179/1eU
THERMAL			
HDT, 0.45 MPa, 3.2 mm, unannealed	121	°C	ASTM D 648
HDT, 1.82 MPa, 3.2mm, unannealed	117	°C	ASTM D 648
CTE, 23°C to 80°C, flow	3.4E-05	1/°C	ISO 11359-2
CTE, 23°C to 80°C, xflow	7.7E-05	1/°C	ISO 11359-2
PHYSICAL			
Density	1.27	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	0.3 – 0.5	%	ASTM D 955

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Mold Shrinkage, xflow, 24 hrs (5)	0.3 – 0.5	%	ASTM D 955
Melt Flow Rate, 300°C/1.2 kgf	13	g/10 min	ASTM D 1238
Melt Flow Rate, 300°C/2.16 kgf	27.5	g/10 min	ASTM D 1238
Water Absorption, (23°C/sat)	0.08	%	ISO 62
Moisture Absorption (23°C / 50% RH)	0.04	%	ISO 62
Melt Volume Rate, MVR at 300°C/1.2 kg	12	cm ³ /10 min	ISO 1133
Melt Volume Rate, MVR at 300°C/2.16 kg	25	cm ³ /10 min	ISO 1133
ELECTRICAL			
Dielectric Constant, 1.1 GHz	3.07	-	SABIC method
Dielectric Constant, 1.9 GHz	3.06	-	SABIC method
Dielectric Constant, 5 GHz	3.06	-	SABIC method
Dielectric Constant, 10 GHz	3.05	-	SABIC method
Dissipation Factor, 1.1 GHz	0.0067	-	SABIC method
Dissipation Factor, 1.9 GHz	0.0065	-	SABIC method
Dissipation Factor, 5 GHz	0.0069	-	SABIC method
Dissipation Factor, 10 GHz	0.0069	-	SABIC method
FLAME CHARACTERISTICS			
UL Recognized, 94V-2 Flame Class Rating (3)	0.3	mm	UL 94
UL Recognized, 94V-1 Flame Class Rating (3)	0.4	mm	UL 94
UL Recognized, 94V-0 Flame Class Rating (3)	0.6	mm	UL 94
INJECTION MOLDING			
Drying Temperature	110	°C	
Drying Time	3 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	285 – 310	°C	
Nozzle Temperature	285 – 305	°C	
Front - Zone 3 Temperature	280 – 300	°C	
Middle - Zone 2 Temperature	270 – 290	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.1 – 0.3	MPa	
Screw Speed	50 – 90	rpm	



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.