

LNP™ THERMOCOMP™ COMPOUND D351

REGION ASIA

DESCRIPTION

LNP THERMOCOMP D351 (experimental grade name as EXTC8143) is a compound based on Polycarbonate resin containing Glass Fiber, Flame Retardant. Added features of this material include: High modulus, good flatness, good ductility, Non-Brominated & Non-Chlorinated Flame Retardant.

TYPICAL PROPERTY VALUES

Revision 20170913

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
MECHANICAL			
Tensile Stress, brk, Type I, 5 mm/min	120	MPa	ASTM D 638
Tensile Strain, brk, Type I, 5 mm/min	2.4	%	ASTM D 638
Tensile Modulus, 5 mm/min	9040	MPa	ASTM D 638
Flexural Stress, brk, 1.3 mm/min, 50 mm span	179	MPa	ASTM D 790
Flexural Modulus, 1.3 mm/min, 50 mm span	8390	MPa	ASTM D 790
Tensile Stress, break, 5 mm/min	125	MPa	ISO 527
Tensile Modulus, 1 mm/min	9080	MPa	ISO 527
Flexural Stress, yield, 2 mm/min	169	MPa	ISO 178
Flexural Modulus, 2 mm/min	7520	MPa	ISO 178
IMPACT			
Izod Impact, unnotched, 23°C	508	J/m	ASTM D 4812
Izod Impact, notched, 23°C	150	J/m	ASTM D 256
Instrumented Impact Energy @ peak, 23°C	24	J	ASTM D 3763
Charpy 23°C, V-notch Edgew 80*10*4 sp=62mm	15	kJ/m ²	ISO 179/1eA
Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm	39	kJ/m ²	ISO 179/1eU
THERMAL			
HDT, 1.82 MPa, 3.2mm, unannealed	116	°C	ASTM D 648
CTE, -40°C to 40°C, flow	2.02E-05	1/°C	ASTM E 831
CTE, -40°C to 40°C, xflow	6.74E-05	1/°C	ASTM E 831
PHYSICAL			
Density	1.425	g/cm ³	ASTM D 792
Mold Shrinkage, flow, 24 hrs (5)	0.1 – 0.3	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs (5)	0.1 – 0.3	%	ASTM D 955
Melt Flow Rate, 300°C/2.16 kgf	25.2	g/10 min	ASTM D 1238

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Melt Volume Rate, MVR at 300°C/2.16 kg	20	cm ³ /10 min	ISO 1133
FLAME CHARACTERISTICS			
UL Recognized, 94V-0 Flame Class Rating (3)	0.8	mm	UL 94
INJECTION MOLDING			
Drying Temperature	110	°C	
Drying Time	3 – 6	hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	285 – 310	°C	
Nozzle Temperature	285 – 305	°C	
Front - Zone 3 Temperature	280 – 300	°C	
Middle - Zone 2 Temperature	270 – 290	°C	
Rear - Zone 1 Temperature	260 – 280	°C	
Mold Temperature	80 – 110	°C	
Back Pressure	0.1 – 0.3	MPa	
Screw Speed	50 – 90	rpm	

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a “seller”), is made exclusively under seller’s standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer’s particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.