

Sarlink® TPV 3135

Teknor Apex Company - Thermoplastic Vulcanizate

Wednesday, January 21, 2026

General Information

Product Description

SARLINK® TPV 3100 series are engineered materials designed primarily for general purpose, automotive and industrial applications requiring a good balance of thermal, mechanical, and physical properties. SARLINK® 3135 is a low hardness, low density, multi-purpose thermoplastic vulcanizate that can be processed by injection molding, blow molding or extrusion for applications such as grips, seals, gaskets, profiles, hose & tubes, bellows, and other articles.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Bondability • Chemical Resistant • General Purpose • Good Adhesion • Good Flexibility	• Good Moldability • Good Processability • Good Surface Finish • High Elasticity • High Heat Resistance	• High Melt Stability • Low Density • Low Hardness • Low Specific Gravity • Resilient
Uses	• Appliance Components • Automotive Applications • Automotive Exterior Parts • Automotive Interior Parts • Automotive Under the Hood • Blow Molding Applications	• Gaskets • General Purpose • Handles • Industrial Applications • O-rings • Pipe Seals	• Plugs • Profiles • Rubber Replacement • Seals
Agency Ratings	• UL 94		
RoHS Compliance	• RoHS Compliant		
UL File Number	• QMFZ2.E54709		
Appearance	• Natural Color	• Opaque	
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.930	g/cm ³	ASTM D792
Density	0.930	g/cm ³	ISO 1183
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			
Across Flow : 100% Strain	1.10	MPa	ISO 37
Across Flow : 100% Strain	1.10	MPa	ASTM D412
Flow : 100% Strain	2.10	MPa	ISO 37
Flow : 100% Strain	2.10	MPa	ASTM D412
Tensile Stress			
Across Flow : Break	4.00	MPa	ISO 37
Across Flow : Break	4.00	MPa	ASTM D412
Flow : Break	2.20	MPa	ISO 37
Flow : Break	2.20	MPa	ASTM D412
Tensile Elongation			
Across Flow : Break	600	%	ISO 37
Across Flow : Break	600	%	ASTM D412
Flow : Break	200	%	ISO 37
Flow : Break	200	%	ASTM D412

Revision Date: 10/1/2018

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 3135

Teknor Apex Company - Thermoplastic Vulcanizate

Elastomers	Nominal Value	Unit	Test Method
Tear Strength - Across Flow			
--	15.0	kN/m	ASTM D624
-- 2	15.0	kN/m	ISO 34-1
Compression Set			
23°C, 22 hr	15	%	ISO 815
23°C, 22 hr	15	%	ASTM D395
70°C, 22 hr	30	%	ISO 815
70°C, 22 hr	30	%	ASTM D395
125°C, 70 hr	52	%	ISO 815
125°C, 70 hr	52	%	ASTM D395
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			
Shore A, 5 sec, Extruded	38		ISO 868
Shore A, 5 sec, Extruded	38		ASTM D2240
Shore A, 5 sec, Injection Molded	43		ISO 868
Shore A, 5 sec, Injection Molded	43		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
RTI Elec	50.0	°C	UL 746B
RTI Imp	50.0	°C	UL 746B
RTI Str	50.0	°C	UL 746B
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air - Across Flow			
135°C, 1000 hr	0.0	%	ISO 188
135°C, 1000 hr	0.0	%	ASTM D573
100% Strain 135°C, 1000 hr	4.0	%	ISO 188
100% Strain 135°C, 1000 hr	4.0	%	ASTM D573
150°C, 168 hr	4.0	%	ISO 188
150°C, 168 hr	4.0	%	ASTM D573
100% Strain 150°C, 168 hr	11	%	ISO 188
100% Strain 150°C, 168 hr	11	%	ASTM D573
Change in Tensile Strain at Break in Air - Across Flow			
135°C, 1000 hr	-2.0	%	ISO 188
135°C, 1000 hr	-2.0	%	ASTM D573
150°C, 168 hr	1.0	%	ISO 188
150°C, 168 hr	1.0	%	ASTM D573
Change in Shore Hardness in Air			
Shore A, 135°C, 1000 hr	-1.0		ISO 188
Shore A, 135°C, 1000 hr	-1.0		ASTM D573
Shore A, 150°C, 168 hr	1.0		ISO 188
Shore A, 150°C, 168 hr	1.0		ASTM D573
Change in Volume			
125°C, 70 hr, in IRM 903 Oil	150	%	ISO 1817
125°C, 70 hr, in IRM 903 Oil	150	%	ASTM D471
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm, All Colors)	HB		UL 94

Revision Date: 10/1/2018

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 3135

Teknor Apex Company - Thermoplastic Vulcanizate

Additional Information	Nominal Value	Unit	Test Method
Apparent Shear Viscosity - Capillary, @ 206/s			
200°C	270	Pa·s	ISO 11443
200°C	270	Pa·s	ASTM D3835

Legal Statement

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Rear Temperature	177 to 216	°C
Middle Temperature	177 to 216	°C
Front Temperature	177 to 216	°C
Nozzle Temperature	188 to 221	°C
Processing (Melt) Temp	182 to 221	°C
Mold Temperature	10 to 66	°C
Back Pressure	0.0689 to 0.345	MPa
Screw Speed	100 to 200	rpm
Screw L/D Ratio	20.0:1.0	
Extrusion	Nominal Value	Unit
Drying Temperature	82	°C
Drying Time	3.0	hr
Cylinder Zone 1 Temp.	182 to 204	°C
Cylinder Zone 2 Temp.	182 to 204	°C
Cylinder Zone 3 Temp.	188 to 210	°C
Cylinder Zone 4 Temp.	188 to 210	°C
Melt Temperature	193 to 216	°C
Die Temperature	193 to 216	°C
Take-Off Roll	21 to 49	°C

Extrusion Notes

Screen Pack: 20 to 60 Mesh
Screw: General Purpose
Compression Ratio: 3:1

Notes

¹ Typical properties: these are not to be construed as specifications.

² Method Ba, Angle (Unnicked)

Revision Date: 10/1/2018

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Sarlink® TPV 3135

Teknor Apex Company - Thermoplastic Vulcanizate

Teknor Apex Company Corporate Headquarters

In U.S. for Vinyls, TPEs, Colorants,

Engineered Thermoplastics (Chem Polymer)
505 Central Avenue
Pawtucket, Rhode Island 02861 U.S.

Phone: 401-725-8000
Fax: 401-725-8095
Toll Free (U.S. only) 800-556-3864

www.teknorapex.com
info@teknorapex.com

Teknor Apex B.V.

Brightlands Chemelot Campus Umonderbaan
22
6167 RD Geleen, Netherlands

Phone: +31 46 7020 950
Fax: +31 46 7020 990

www.teknorapex.com
tpe@teknorapex.com

Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.

No. 78 Ping Sheng Road

Suzhou Industrial Park
Jiangsu, China 215126

Phone: (86) 512-6287-1550
Fax: (86) 512-6288-8371

www.teknorapex.com
infotaap@teknorapex.com

Teknor Apex Asia Pacific PTE. LTD.

41 Shipyard Road

Singapore 628134

Phone: (65) 6265-2544
Fax: (65) 6265-1821

www.teknorapex.com
infotaap@teknorapex.com

Revision Date: 10/1/2018

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.