

Arnite[®] ACE339 RC–MB

PET–I–GF40

Print Date: 2024–05–14

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	VALUE		
Melt volume–flow rate	15	cm³/10min	ISO 1133
Temperature	290	°C	ISO 1133
Load	10	kg	ISO 1133
MECHANICAL PROPERTIES	VALUE		
Tensile modulus	12100	MPa	ISO 527–1/–2
Stress at break	145	MPa	ISO 527–1/–2
Strain at break	3.7	%	ISO 527–1/–2
Charpy impact strength (+23°C)	85	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	15	kJ/m²	ISO 179/1eA

All the trademarks mentioned here are trademarks of Envalior.
Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.
Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.
Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values.
Copyright © Envalior 2024. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.