



Bayer Uretech

Desmopan DP 3685AU DPS 102

Desmopan 3685AU DPS 102 is a special ester-based transparent thermoplastic polyurethane which is designed for injection molding, UV stabilized. It offers excellent mechanical properties and transparency within 6mm of thickness.

Preliminary Data Sheet

Properties	DIN	UNIT	
Tensile Strength	53504	N/mm ²	51
Elongation	53504	%	450
Hardness	53505	Shore A	86
100% Modulus	53504	N/mm ²	6
Density	53479	g/cm ³	1.20
Tear Strength	53515	N/mm	100
Abrasion Loss	53516	mm ³	50
Recommended Processing Temp.		°C	190~210

This information and our technical advice whether verbal, in writing or by way of trials are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided especially that contained in our safety data and technical information sheets and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery

2008-6-2

Process Information

3685AUX

Drying temp 100C

Drying time:for dehumidified dryer,1-2hour should be OK;

for cycling hot air dryer,3-4hour,it depended on the relative humidity of enviornment;

for hot oven,you'd better spread the material to no more than 2cm thick.

After drying:dried,hot granules should not be left to cool down in the open air,they must be stored in container which can be re-sealed,the hopper must be covered over.

Suggested max moisture:0.05%

Suggested max regrind:30%,depend on the function of your part,which should be tested before used as a real part.

Barrel Temp:nozzle 190-210,middle&front 180-190,rear 170

Processing temp:190-210C

Mold temp:normally,20-40C will be used,with thick-walled articles,cooling down to approx.5C can bring a reduction in cycle time.

Injection speed:depend promarily on the wall thickness,in general,thick-walled articles require slow filling of the mold,and thin-walled articles fast filling.

Back pressure:5-15bar

Screw speed:peripheral velocity of the screw shouldn't exceed 0.3m/s

Clamp tonage:depend on size of the part

Cushion:3-6mm

Screw L/D Ratio:18:1-20:1

Screw Compression Ratio:2:1-2.5:1

Vent Depth:0.02mm

欣阳塑胶工业(天津)有限公司	
部门 <u>SGE</u>	日期 <u>02 JUN 2003</u>
发行	
版本号 <u>08.6.2</u>	副本号 <u>02</u>

陈景华
李安志
2008.6.2