

PRODUCT INSPECTION SHEET

Customer	-	Report No.	SAM23080205
Material	PP+F/R V0,halogen free	Lot No.	-
Grade Name	FH63NHCK369	Color	Customer black
Spec.	Halogen free F/R V0	Date of Issue	--

Properties	Test Method	Test Condition	Unit	Value
Melt Index (熔融指数)	ASTM D1238	230℃,2.16kg	g/10min	10.6
Density (密度)	ASTM D792	-	g/cm ³	0.99
Tensile strength at Yield (拉伸强度)	ASTM D638	Speed :50mm/min	kg/ cm2	328
Elongation (Break) (断裂伸长率)	ASTM D638		%	7.4
Flexural Modulus (弯曲模量)	ASTM D790	Speed :50mm/min	kg/ cm2	20,412
IZOD Impact strength (悬臂梁冲击强度, 缺口)	ASTM D256	23℃	kg/ cm2	2.8
Heat Deflection Temp. (热变形温度)	ASTM D648	Load 4.6kgf	℃	120
Surface hardness (洛氏硬度)	ASTM D785	Rockwell	R-Scale	--
Mold Shrinkage (模具收缩率)	Hanwha total	2mmt	1/1000	12
Flame Resistance (阻燃性)		1.5mm		V0

The standard values Indicated in the table only describe typical properties, but do not constitute specification limits.