



CHI MEI CORPORATION

59-1 SAN CHIA, JEN TE, TAINAN COUNTY, TAIWAN R.O.C.

TEL: 886-6-266-5000,

FAX: 886-6-266-5555~7

防火級 ABS, POLYLAC[®] PA-765A

V1W

材料特性

特性(Properties)	測試方法(Test Method)	測試條件(Test Condition)	單位(Unit)	PA-765A
引張強度 Tensile Strength	ASTM D638	1/8", 6 mm/min	Kg/cm ² (lb/in ²)	400(5670)
延伸率 Tensile Elongation	ASTM D638	1/8", 6 mm/min	%	15
彎曲強度 Flexural Strength	ASTM D790	1/4", 2.8 mm/min	Kg/cm ² (lb/in ²)	640(9070)
彎曲彈性率 Flexural Modulus	ASTM D790	1/4", 2.8 mm/min	Kg/cm ² (lb/in ²)	23000(320000)
IZOD 衝擊強度 Izod Impact Strength	ASTM D256(Notched)	1/4", 23°C 1/8", 23°C	Kg-cm/cm(ft-lb/in) Kg-cm/cm(ft-lb/in)	20(3.7) 24(4.4)
流動係數 Melt Flow Index	ASTM D1238	200°C , 5Kg	g/10min	4.8
硬度 Hardness	ASTM D785	1/2"	R Scale	100
比重 Specific Gravity	ASTM D792	23°C	-	1.17
軟化點 Vicat Softening Temp	ASTM D1525	1/8", 50°C /hr	°C (°F)	92(198)
熱變形溫度 H.D.T Annealed(85°C , 8hr) Unannealed	ASTM D648	1/4", 120°C /hr	°C (°F)	85(185) 76(169)
燃燒率 Flammability	UL 94	1/16"	-	1/12"V-0 1/10"5VA 1/12"5VB

以上數據僅代表一般通用數據，不代表每一產品的規格值

若有任何疑問請洽產品推廣課 06-2665000, 06-2663000