

# 科技引领弹性体

## ETflex™

### ET1295 NT001



ET Elastomer

Print Date: 2021/11/26

Description: Thermoplastic Elastomer, designed for over-molding with ABS、PC, High intensity.

| Physical                      | Test method | Unit              | Typical value |
|-------------------------------|-------------|-------------------|---------------|
| Specific gravity              | ASTM 792    | g/cm <sup>3</sup> | 1.22          |
| Shore A hardness              | ASTM D2240  | Shore A           | 95            |
| Flow ability                  | Test method | Unit              | Typical value |
| Melt Flow Rate (230℃, 2.16Kg) | ASTM 1238   | g/10min           | -             |
| Mechanical                    | Test method | Unit              | Typical value |
| Tensile strength (break)      | ASTM D412   | MPa               | 40.5          |
| Tensile strength (100%)       | ASTM D412   | MPa               | 7.5           |
| Tensile strength (300%)       | ASTM D412   | MPa               | 17.5          |
| Tensile elongation (Break)    | ASTM D412   | %                 | 750           |
| Flammability                  | Test method | Flame class       | Min. Thk.     |
| Flammability                  | UL94        | -                 | -             |
| Drying condition              | Unit        | Typical value     |               |
| Dry temperature               | ℃           | 80-100            |               |
| Dry time                      | Hr.         | 3~4               |               |
| Injection condition           | Unit        | Typical value     |               |
| Melt temperature              | ℃           | 180~210           |               |
| Barrel temperature            | ℃           | 180~210           |               |
| Nozzle temperature            | ℃           | 190~220           |               |
| Mold temperature              | ℃           | 20~50             |               |
| Disclaimer                    |             |                   |               |

The data and information is based on our current knowledge and experience and is for guidance only. Since the conditions of use and applicable laws may vary from time to time, it is the responsibility of users to determine whether the products and product information in this document are suitable for the use of the user and to test whether our products are suitable for their use. E.T recommends that users investigate the end use of their products in advance to ensure that they can use the product correctly. Users can request the material safety data sheet (MSDS) from the local sales of E.T. E.T does not assume any responsibility or obligation for the data and information, nor does it provide any assurance. All implied warranties are expressly excluded here.

Guangzhou E.T Material Technology Co., Ltd

Address: Hong Tai Wisdom Valley, No.23 Sicheng Rd,Tianhe District,Guangzhou

Email: sales@etelastomer.com