

科技引领弹性体

ETflex™

ET3270D NT006



ET Elastomer

Print Date: 2021/11/26

Description: Thermoplastic elastomers.

Physical	Test method	Unit	Typical value
Specific gravity	ASTM 792	g/cm ³	1.29
Hardness(5sec)	ASTM D2240	Shore D	70
Flow ability	Test method	Unit	Typical value
Melt Flow Rate(230℃,2.16Kg)	ASTM 1238	g/10min	18
Mechanical	Test method	Unit	Typical value
Tensile strength (break)	ASTM D412	MPa	43
Tensile strength (100%)	ASTM D412	MPa	26
Tensile strength (300%)	ASTM D412	MPa	-
Tensile elongation (Break)	ASTM D412	%	250
Tear strength	ASTM D624	kN/m	-
Drying condition	Unit	Typical value	
Dry temperature	℃	100-110	
Dry time	Hr.	3-4	
Injection condition	Unit	Typical value	
Melt temperature	℃	230~250	
Barrel temperature	℃	210~250	
Nozzle temperature	℃	230~250	
Mold temperature	℃	20~50	
Disclaimer			

The data and information is based on our current knowledge and experience and is for guidance only. Since the conditions of use and applicable laws may vary from time to time, it is the responsibility of users to determine whether the products and product information in this document are suitable for the use of the user and to test whether our products are suitable for their use. E.T recommends that users investigate the end use of their products in advance to ensure that they can use the product correctly. Users can request the material safety data sheet (MSDS) from the local sales of E.T. E.T does not assume any responsibility or obligation for the data and information, nor does it provide any assurance. All implied warranties are expressly excluded here.

Guangzhou E.T Material Technology Co., Ltd

Address: Hong Tai Wisdom Valley, No.23 Sicheng Rd,Tianhe District,Guangzhou

Email: sales@etelastomer.com