

HanWha TOTAL PP Compound

BJ75U

■Grade: BJ75U

■Characteristics: Good Mechanical strength & Heat resistance, Good Processing,
Good UV Resistant.

Properties	Test Method	Test Condition	Unit	Result
Melt Index	ISO R1133	230°C, 2.16kg	g/10min	26
Density	ISO R1183	-	g/cm ³	0.902
Tensile strength at Yield	ISO R527	Speed :50mm/min	MPa	25
Elongation (Break)			%	120
Flexural Modulus	ISO R178	Span 60mm Speed 2mm/min	MPa	1280
Izod Impact strength	ISO R180	t=4mm Notched	kJ/m ²	7.5
Heat Deflection Temp.	ISO R75	Load 4.6kgf	°C	98
Shrinkage ratio	STC Method	300x90x3t	X 1/1000	15-17

※ Property Value above is subject to change depend on processing condition.

HanWha TOTAL PETROCHEMICALS CO.