

PRODUCT INSPECTION SHEET

Customer	-	Car Model	PP-SGF20(FR)
Grade Name	FB55G	Color	Nature color
Lot No	-	Date of Issue	2022-07-19

Properties	Test Method	Test Condition	Unit	Value
Melt Index (熔融指数)	ASTM D1238	230℃,2.16kg	g/10min	5
Density (密度)	ASTM D792	-	g/cm ³	1.36
Tensile strength at Yield (拉伸强度)	ASTM D638	Speed :50mm/min	kg/ cm2	730
Elongation (Break) (断裂伸长率)	ASTM D638		%	3
Flexural Modulus (弯曲模量)	ASTM D790	Speed :50mm/min	kg/ cm2	55,000
IZOD Impact strength (悬臂梁冲击强度, 缺口)	ASTM D256	23℃	kg/ cm2	12
Heat Deflection Temp. (热变形温度)	ASTM D648	Load 4.6kgf	℃	163
Surface hardness (洛氏硬度)	ASTM D785	Rockwell	R-Scale	100
Mold Shrinkage (模具收缩率)	Hanwha total	1/1,000	%	3~9
Flame Resistance (阻燃性)	UL94	0.75、1.5、3.0mm	-	V-0