

PRODUCT INSPECTION SHEET

Customer	-	Car Model	
Grade Name	GH43U	Color	Nature color
Lot No	-	Date of Issue	-

Properties	Test Method	Test Condition	Unit	Value
Melt Index	ASTM D1238	230°C, 2.16kg	g/10min	5.0
Density	ASTM D792	-	g/cm ³	1.13
Tensile strength at Yield	ASTM D638	Speed	kg/ cm ²	1100
Elongation (Break)	ASTM D638	:50mm/min	%	3
Flextural modulus	ASTM D790	Speed :50mm/min	kg/ cm ²	60,000
IZOD Impact strength	ASTM D256	23°C	Kg cm/cm	13
Heat Deflection Temp.	ASTM D648	Load 4.6kgf	°C	163
Surface hardness	ASTM D785	Rockwell	R-Scale	115
Mold Shrinkage	Hanwha total	2mmt	%	0.2~0.9
Non-flammability	UL-94	-	-	HB (1/16")
Weather ability (anti-UV)		-Xenon-ARC -BP Tem(63°C) -0~3000hr aging	1000hrs 2000hrs 3000hrs	ΔE:0.55 ΔE:0.72 ΔE:1.02

The standard values Indicated in the table only describe typical properties, but do not constitute specification limits.

General Processing Guide

► Typical Processing Conditions are as follows.

- Feeding zone temperature: 180 ~ 200 °C
- Plasticizing zone temperature: 190 ~ 210 °C
- Measuring zone temperature: 200 ~ 220 °C
- Mold temperature: 40 ~ 80 °C
- Screw rpm: 30 ~ 80
- Injection pressure: 600 ~ 1,000 kg/cm²
- Holding pressure: 400 ~ 900 kg/cm²

Actual injection conditions must be adjusted according to the types of injection machines and sizes of molds and parts.