



南亞塑膠工業股份有限公司

NAN YA PLASTICS CORPORATION

NAN YA FR-NYLON66 PRODUCT INFORMATION

GRADE : 6410G3

Product Description : Flame Retarded, 15%Glass Fiber Reinforced Nylon66
 High Mechanical Strength
 High Abrasion Resistance & Machineability
 Good Thermal Resistance & Fatigue Resistance
 UL94 0.75mm V0.

PROPERTIES		TEST METHOD	UNIT	REF. VALUE	REFERENCE MOLDING CONDITIONS		
1.Physical					Drying Time	Hrs	4
Tensile Strength at Yield	ASTM D-638	kg/cm ²	1200		Drying Temp.	℃	80
Elongation	ASTM D-638	%	2.4		Cylinder Temp. Rear Center Front		
Flexural Strength	ASTM D-790	kg/cm ²	1850			℃	270
Flexural Modulus	ASTM D-790	kg/cm ²	72000			℃	275
IZOD Impact (Notched)	ASTM D-256	kg-cm/cm	8.5			℃	280
Rockwell Hardness	ASTM D-785	R-Scale	120		Nozzle Temp.	℃	285
2.Thermal					Mold Temp.	℃	85~95
Melting Point	DSC	℃	262		Injection Pressure	kg/cm ²	450-1000
H.D.T.(18.6 kg/cm2)	ASTM D-648	℃	240		Screw Rotation speed	rpm	180
Melting Flow Index (MFI)	ASTM D-1238	g/10 min	26		Injection Speed	--	fast
3.Electrical					Injection M/C : 3 OZ FT-60 Mold : ASTM Test Bar Gate Size: 5.8mm×1.2mm Test Bar Thickness : 3.0mm Test Condition: 23℃ , 50%RH		
Volume Resistivity	ASTM D-257	Ω • cm	10 ¹⁵				
Dielectric Strength	ASTM D-149	kv/mm	18				
Dielectric Constant (10 ⁶ HZ)	ASTM D-150	--	3.2				
Dissipation Factor (10 ⁶ HZ)	ASTM D-150	--	0.02				
Arc Resistance	ASTM D-495	sec.	70		NAN YA PLASTICS CORPORATION PLASTICS 3rd DIVISION ENGINEERING PLASTICS DEPT. TEL:886-2-27122211ext.5814 FAX:886-2-27198661		
4.Others							
Specific Gravity	ASTM D-792	--	1.56				
Mold Shrinkage (MD)	3 mmt	%	0.5				
Mold Shrinkage (TD)	3 mmt	%	1.0				
Flammability	UL 94	--	V-0				
Remarks	UL FILE NO. :E130155(M)						

Melting Flow Index Test Condition: 275°C×2.16Kg

The values in this table are for reference only.

2020/7/24