

POLYWING

Data sheet

Valumid A1NG6 BK00001

Description

30% glass fiber reinforced, injection grade PA66, high hardness and rigidity, high HDT, good impact strength, easy processing, especially for electrical and electronic components, automobile radiator, intake manifold, connectors, sensors, bobbin etc.,

Physical	Test method	Unit	Typical value
Specific gravity	ISO 1183-1	g/cm ³	1.40
Water absorption (23°C,24h)	ISO 62	%	1.20
Flow ability	Test method	Unit	Typical value
Melt Flow Rate	ISO 1133	g/10min	-
Mechanical	Test method	Unit	Typical value
Tensile strength (50mm/min)	ISO 527	MPa	165
Elongation at break (50mm/min)	ISO 527	%	2.8
Flexural strength (2mm/min)	ISO 178	MPa	260
Flexural modulus (2mm/min)	ISO 178	MPa	9300
Charpy impact strength(notched)	ISO 179	kJ/m ²	18
Charpy impact strength(unnotched)	ISO 179	kJ/m ²	85
Thermal	Test method	Unit	Typical value
Melting point	-	°C	-
HDT (1.82MPa)	ISO 75	°C	245
Electrical	Test method	Unit	Typical value
CTI	IEC 60112	V	550
Volume resistivity	IEC 60093	Ω•m	1E+13
Dissipation factor (1MHz)	IEC 60250	-	0.03
Dielectric constant (1MHz)	IEC 60250	-	3.2
Electric strength	IEC 60243-1	kV/mm	32
Flammability	Test method	Unit	Typical value
Flammability UL94HB	UL94	mm	1.5
RTI	UL 746B		
Elec		°C	-
Imp		°C	-
Str		°C	-
Others	Test method	Unit	Typical value
Reinforced	-	%	30
Molding shrinkage	ISO 294-4	%	0.4~0.7
GWFI	IEC 60335 1-2	°C	-

Drying condition	Unit	Typical value
Dry temperature	°C	90~120
Dry time	Hr.	4-6
Injection condition	Unit	Typical value
Melt temperature	°C	260~285
Barrel temperature	°C	250~275
Nozzle temperature	°C	265~290
Mold temperature	°C	60~90
Injection pressure	MPa	90~120
Disclaimer		

The data and information is based on our current knowledge and experience and is for guidance only. Since the conditions of use and applicable laws may vary from time to time, it is the responsibility of users to determine whether the products and product information in this document are suitable for the use of the user and to test whether our products are suitable for their use. Baoyan recommends that users investigate the end use of their products in advance to ensure that they can use the product correctly. Users can request the material safety data sheet (MSDS) from the local sales of Baoyan. Baoyan does not assume any responsibility or obligation for the data and information, nor does it provide any assurance. All implied warranties are expressly excluded here.

Guangzhou Polywing New Material Co., Ltd
Address: Hong Tai Wisdom Valley, No.19 Sicheng Rd.,
Tianhe District, Guangzhou
Email: sales@polywingtech.com
Website: <http://www.polywingtech.com>

