

POLYWING

物性表 Technical Data Sheet

Valupoly PGB6060 BK90001

产品说明 Description

PP, 30% (玻纤+玻璃珠增强)、注塑级。

PP, 30% (GF+GB)、injection molding.

性能 Properties	测试条件 Test Condition	测试标准 Test Standard	单位 Unit	典型值 Typical Value
------------------	------------------------	-----------------------	------------	----------------------

物理性能 Physical

密度 Density	23℃	ISO 1183-1	g/cm ³	1.09
填充比例 Reinforced		ISO 2577	%	30
成型收缩率 Molding shrinkage		ISO 294-4	%	0.7~1.0

机械性能 Mechanical

拉伸强度 Tensile strength	5mm/min	ISO 527	MPa	40
断裂伸长率 Elongation at break	5mm/min	ISO 527	%	5.0
弯曲强度 Flexural strength	2mm/min	ISO 178	MPa	45
弯曲模量 Flexural modulus	2mm/min	ISO 178	MPa	2,000
悬臂梁缺口冲击强度 Izod impact strength (notched)	4mm	ISO 180	kJ/m ²	12

热性能 Thermal

热变形温度 HDT	1.8MPa	ISO 75	℃	100
阻燃等级 Flame Rating	0.8mm	UL 94	-	HB

材料工艺指南 Processing Technology Guide	单位 Unit	范围 Typical value
烘干温度 Dry temperature	℃	80~100
烘干时间 Dry time	H	2~4
熔体温度 Melt temperature	℃	200~240
模具温度 Mold temperature	℃	40~80
免责声明 Disclaimer		

本文本的数据与信息是基于我们现在的认识与经验，仅供指导。由于使用条件和适用法律可能因地因时而异，用户有责任确定本文件里的产品和产品信息是否适合用户使用，并且测试我们的产品是否适合用户的用途。宝研建议用户事先调查自己产品的最终用途，以保证能正确使用该产品，用户可向当地的宝研销售人员索取本产品的材料安全数据表（MSDS）。宝研对文本信息不承担任何责任与义务，也未提供任何保证，对所有默示保证在此明确地予以排除。

The data and information is based on our current knowledge and experience and is for guidance only. Since the conditions of use and applicable laws may vary from time to time, it is the responsibility of users to determine whether the products and product information in this document are suitable for the use of the user and to test whether our products are suitable for their use. Polywing recommends that users investigate the end use of their products in advance to ensure that they can use the product correctly. Users can request the material safety data sheet (MSDS) from the local sales of Polywing. Polywing does not assume any responsibility or obligation for the data and information, nor does it provide any assurance. All implied warranties are expressly excluded here.

广州宝研新材料有限公司

Guangzhou Polywing New Material Co., Ltd.

天河区思成路 19 号宏太智慧谷

Hong Tai Wisdom Valley, No.19 Sicheng Rd., Tianhe District, Guangzhou

邮箱/Email: sales@polywingtech.com

网址/Website: <http://www.polywingtech.com>

POLYWINGTM
focus on quality