

PRODUCT INFORMATION

RADILON A RV300RG 3900 BK

DESCRIPTION

PA66 30% glass fiber reinforced injection moulding grade. Heat stabilized, high hydrolysis resistance. Deep black colour.

Suitable for parts requiring high stiffness and good mechanical resistance. Particularly fit to work in contact with automotive cooling circuit liquids.

ISO 1043: PA66-T GF30

REGIONAL AVAILABILITY: North America, Europe, Asia Pacific, South and Central America, Near East/Africa

MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature
280 - 300°C

Mold Temperature
80 - 100°C

Injection Speed
medium-high

PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet
ROHS compliant 2011/65/UE and following amendments

TECHNICAL DATA SHEET

RADILON A RV300RG 3900 BK

PROPERTY	STANDARD	UNIT	VALUE	DAM*	Cond**
PHYSICAL PROPERTIES					
Density		kg/m ³	1370		
Moulding shrinkage - Parallel / Normal	300 / 90 / 60 ^[1]	%	0.3 / 1.0		
Water Absorption, immersion at 23°C	2mm	%	7		
Moisture Absorption 23°C - 50%RH	2mm	%	1.7		
MECHANICAL PROPERTIES					
Tensile Modulus	1mm/min	MPa	9950	8000	
Stress at Break	5mm/min	MPa	195	135	
Strain at Break	5mm/min	%	3.7	3.7	
Flexural Modulus	2mm/min	MPa	9000		
Flexural Strength	2mm/min	MPa	295		
Charpy Impact Strength	+23°C	kJ/m ²	95	105	
Charpy Notched Impact Strength	+23°C	kJ/m ²	14	15	
Charpy Notched Impact Strength	-30°C	kJ/m ²	12		
THERMAL PROPERTIES					
Melting Temperature	10°C/min	°C	260		
Heat Deflection Temperature	1.80 MPa	°C	240		
Vicat Softening Temperature	50°C/h 50N	°C	250		
FLAMMABILITY PROPERTIES					
Flammability	0.8mm	class	HB		
Glow Wire Flammability Index	2mm	°C	700		
Automotive Interior Flammability	3mm	mm/min	0		
ELECTRICAL PROPERTIES					
Volume Resistivity	500V	Ohm*m	1E13	1E11	
Surface Resistivity	500V	Ohm	1E12	1E10	

*: DAM = Dry As Moulded state according to ISO 16396-2 **: Cond = Conditioned state similar to ISO 1110 1: Melt Temperature [°C] / Mold Temperature [°C] / Cavity Pressure [MPa]