

LEXAN™ Resin HF1110R - Asia

Polycarbonate
SABIC

PROSPECTOR®

www.ulprospector.com

Technical Data

Product Description

LEXAN™ HF1110R resin is a 25 MFR polycarbonate, MVR of 26. Mold release. UL94 V2 rated.

General

Material Status	• Commercial: Active		
UL Yellow Card ¹	• E45587-236896 • E207780-100726492		
Search for UL Yellow Card	• SABIC • LEXAN™ Resin		
Availability	• Asia Pacific		
Uses	• Appliances • Automotive Exterior Parts • Automotive Interior Parts • Automotive Lighting • Construction Applications • Electrical Parts	• Electrical/Electronic Applications • Electronic Displays • Lighting Applications • Medical Devices • Non-specific Food Applications • Personal Care	• Pharmaceuticals • Recreational Vehicle Applications • Semiconductor Applications • Sporting Goods
Also Available In	• Europe	• Latin America	• North America

Physical	Nominal Value Unit	Test Method
Density / Specific Gravity	1.20 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	25 g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70 %	Internal Method
Mechanical	Nominal Value Unit	Test Method
Tensile Strength ³		ASTM D638
Yield	62.0 MPa	
Break	65.0 MPa	
Tensile Elongation ³ (Break)	120 %	ASTM D638
Flexural Modulus ⁴ (50.0 mm Span)	2300 MPa	ASTM D790
Flexural Strength ⁴ (Yield, 50.0 mm Span)	93.0 MPa	ASTM D790
Impact	Nominal Value Unit	Test Method
Notched Izod Impact (23°C)	640 J/m	ASTM D256
Instrumented Dart Impact 23°C, Energy at Peak	54.0 J	ASTM D3763
Tensile Impact Strength ⁵	378 kJ/m ²	ASTM D1822
Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed, 3.20 mm	126 °C	ASTM D648
RTI Elec	130 °C	UL 746B
RTI Imp	130 °C	UL 746B
RTI Str	130 °C	UL 746B
Electrical	Nominal Value Unit	Test Method
Comparative Tracking Index (CTI)	PLC 2	UL 746A
High Amp Arc Ignition (HAI) ⁶	PLC 1	UL 746A
High Voltage Arc Resistance to Ignition (HVAR)	PLC 2	UL 746A
Hot-wire Ignition (HWI)	PLC 2	UL 746A



Flammability	Nominal Value Unit	Test Method
Flame Rating (1.1 mm)	V-2	UL 94
Optical	Nominal Value Unit	Test Method
Light Transmittance (2540 µm)	88.0 %	ASTM D1003
Haze (2540 µm)	1.00 %	ASTM D1003
Injection	Nominal Value Unit	
Drying Temperature	120 °C	
Drying Time	3.0 to 4.0 hr	
Suggested Max Moisture	0.020 %	
Suggested Shot Size	40 to 60 %	
Rear Temperature	250 to 270 °C	
Middle Temperature	260 to 280 °C	
Front Temperature	270 to 295 °C	
Nozzle Temperature	265 to 290 °C	
Processing (Melt) Temp	270 to 295 °C	
Mold Temperature	70 to 95 °C	
Back Pressure	0.300 to 0.700 MPa	
Screw Speed	40 to 70 rpm	
Vent Depth	0.025 to 0.076 mm	
Injection Notes		
• Drying Time (Cumulative): 48 hr		

- Notes**
- ¹ A UL Yellow Card contains UL-verified flammability and electrical characteristics. UL Prospector continually works to link Yellow Cards to individual plastic materials in Prospector, however this list may not include all of the appropriate links. It is important that you verify the association between these Yellow Cards and the plastic material found in Prospector. For a complete listing of Yellow Cards, visit the UL Yellow Card Search.
- ² Typical properties: these are not to be construed as specifications.
- ³ Type I, 50 mm/min
- ⁴ 1.3 mm/min
- ⁵ Type S
- ⁶ Surface

Where to Buy

Supplier

SABIC
Web: <http://www.sabic.com/>

Distributor

Please contact the supplier to find a distributor for LEXAN™ Resin HF1110R - Asia

