

LNP™ LUBRICOMP™ UFL36AS compound

Monday, August 21, 2017

General Information

Product Description

LNP LUBRICOMP UFL36AS is a compound based on Polyphthalamide resin containing Glass Fiber, PTFE. Added features include Internally Lubricated, Heat Stabilized.

Also known as: LNP* LUBRICOMP* Compound UFL-4036 A HS

Product reorder name: UFL36AS

General

Material Status	• Commercial: Active
Availability	• Europe
Filler / Reinforcement	• Glass Fiber
Additive	• Heat Stabilizer • PTFE Lubricant
Features	• Heat Stabilized • Lubricated
RoHS Compliance	• RoHS Compliant
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.54	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (340°C/2.16 kg)	0.793 to 1.22	in ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow : 24 hr	0.72	%	
Flow : 24 hr	0.21	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.54E+6	psi	ISO 527-2/1
Tensile Stress (Break)	27600	psi	ISO 527-2/5
Tensile Strain (Break)	2.1	%	ISO 527-2/5
Flexural Modulus ²			ISO 178
--	1.33E+6	psi	
176°F	1.22E+6	psi	
212°F	1.10E+6	psi	
248°F	783000	psi	
302°F	551000	psi	
356°F	508000	psi	
392°F	450000	psi	

Disclaimer : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

© 2017 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

LNP™ LUBRICOMP™ UFL36AS compound

SABIC Innovative Plastics Europe - Polyphthalamide

Mechanical	Nominal Value	Unit	Test Method
Flexural Stress ^{2, 3}			ISO 178
--	36400	psi	
176°F	31000	psi	
212°F	28100	psi	
248°F	20500	psi	
302°F	14100	psi	
356°F	11900	psi	
392°F	10300	psi	
Flexural Strain at Break ⁴			ISO 178
--	2.8	%	
176°F	3.1	%	
212°F	3.9	%	
248°F	5.3	%	
302°F	5.0	%	
356°F	4.8	%	
392°F	4.8	%	
Coefficient of Friction			ASTM D3702 Modified
Dynamic	0.48		
Static	0.52		
Wear Factor - Washer	5.00	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-40°F ⁵	5.7	ft-lb/in ²	
73°F ⁶	5.7	ft-lb/in ²	
Unnotched Izod Impact Strength ⁶			ISO 180/1U
-40°F	21	ft-lb/in ²	
73°F	24	ft-lb/in ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁷			ISO 75-2/Af
264 psi, Unannealed, 2.52 in Span	536	°F	
CLTE - Flow (73 to 140°F)	1.2E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 140°F)	3.2E-5	in/in/°F	ISO 11359-2
Specific Heat	0.412	Btu/lb°F	ASTM E1269
Thermal Conductivity	1.7	Btu·in/hr/ft ² /°F	ASTM D5930

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	250 to 300	°F
Drying Time	4.0	hr
Suggested Max Moisture	0.15	%
Rear Temperature	590 to 610	°F
Middle Temperature	600 to 620	°F

Disclaimer : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

© 2017 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

LNP™ LUBRICOMP™ UFL36AS compound

SABIC Innovative Plastics Europe - Polyphthalamide

Injection	Nominal Value	Unit
Front Temperature	620 to 640	°F
Processing (Melt) Temp	600 to 630	°F
Mold Temperature	280 to 330	°F
Back Pressure	25.0 to 50.0	psi
Screw Speed	30 to 60	rpm

Notes

¹ Typical properties: these are not to be construed as specifications.
² 0.079 in/min
³ Yield
⁴ 2 mm/min
⁵ 80*10*3
⁶ 80*10*4
⁷ 80*10*4 mm

Disclaimer : THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES (“SELLER”) ARE SOLD SUBJECT TO SELLER’S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER’S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER’S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller’s materials, products, services or recommendations for the user’s particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller’s Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

© 2017 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.