



Preliminary Experimental Data Sheet

LNP™ ELCRES™ ER016707

TYPICAL PROPERTIES	TYPICAL VALUE	UNIT	STANDARD
MECHANICAL			
Tensile Modulus, 50 mm/min	2382	MPa	ASTM D 638
Tensile Stress, yld, 50 mm/min	71	MPa	ASTM D 638
Tensile Elongation, yld, 50 mm/min	7.1	%	ASTM D 638
Tensile Stress, brk, 50 mm/min	70	MPa	ASTM D 638
Tensile Elongation, brk, 50 mm/min	148	%	ASTM D 638
Izod Impact, notched, 23°C	63	J/m	ASTM D 256
Multiaxial Impact, Total Energy, 23°C	72	J	ASTM D3763
Multiaxial Impact, Total Energy, 0°C	74	J	ASTM D3763
OPTICAL			
Spectral Gloss, 20°	105	%	ASTM D2457
Spectral Gloss, 60°	103	%	ASTM D2457
Spectral Gloss, 85°	96	%	ASTM D 523
Transmission, 1 mm	91	%	ASTM D 1003
Haze, 1 mm	1.1	%	ASTM D 1003
PHYSICAL			
Melt Volume-flow Rate 300°C, 1.2kg	14	cm ³ /10 min	ASTM D 1238

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA DISCLAIMER : THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com>. AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.