

XENYO™ Resin 6370 - Asia

Polycarbonate + PBT

SABIC

PROSPECTOR®

www.ulprospector.com

Technical Data

Product Description

30% glass-reinforced, impact modified thermoplastic alloy. Improved toughness and ductility.

General

Material Status	• Commercial: Active		
Search for UL Yellow Card	• SABIC • XENYO™ Resin		
Availability	• Asia Pacific		
Uses	• Appliances • Automotive Lighting • Automotive Under the Hood • Electrical Parts	• Electrical/Electronic Applications • Electronic Displays • Heavy Transportation • Lawn and Garden Equipment	• Medical/Healthcare Applications • Military/Defense Applications • Outdoor Applications
Also Available In	• Europe	• Latin America	• North America

Physical	Nominal Value Unit	Test Method
Density / Specific Gravity	1.44 g/cm³	ASTM D792 ISO 1183
Specific Volume	0.700 cm³/g	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/5.0 kg)	24 g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR)		ISO 1133
250°C/5.0 kg	12 cm³/10min	
265°C/5.0 kg	19 cm³/10min	
Molding Shrinkage		Internal Method
Across Flow : 0.750 to 2.30 mm	0.40 to 0.70 %	
Flow : 0.750 to 2.30 mm	0.30 to 0.40 %	
Across Flow : 2.30 to 4.60 mm	0.70 to 0.90 %	
Flow : 2.30 to 4.60 mm	0.40 to 0.50 %	
Water Absorption		
24 hr, 23°C	0.090 %	ASTM D570
Saturation, 23°C	0.50 %	ISO 62
Equilibrium, 23°C, 50% RH	0.15 %	ISO 62

Mechanical	Nominal Value Unit	Test Method
Tensile Modulus		
-- ²	9750 MPa	ASTM D638
--	8500 MPa	ISO 527-1/1
Tensile Strength		
Yield ³	97.0 MPa	ASTM D638
Yield	105 MPa	ISO 527-2/5
Break ³	91.0 MPa	ASTM D638
Break	105 MPa	ISO 527-2/5
Tensile Elongation		
Yield ³	3.0 %	ASTM D638
Yield	3.0 %	ISO 527-2/5
Break ³	4.0 %	ASTM D638
Break	3.0 %	ISO 527-2/5
Flexural Modulus		
50.0 mm Span ⁴	5370 MPa	ASTM D790
-- ⁵	7750 MPa	ISO 178



XENOY™ Resin 6370 - Asia

Polycarbonate + PBT

SABIC**PROSPECTOR®**

www.ulprospector.com

Mechanical	Nominal Value Unit	Test Method
Flexural Stress		
-- 5, 6	154 MPa	ISO 178
Yield, 50.0 mm Span ⁴	150 MPa	ASTM D790
Break, 50.0 mm Span ⁴	138 MPa	ASTM D790
Impact	Nominal Value Unit	Test Method
Charpy Notched Impact Strength ⁷ (23°C)	9.0 kJ/m ²	ISO 179/1eA
Notched Izod Impact		
-30°C	110 J/m	ASTM D256
23°C	170 J/m	ASTM D256
-30°C ⁸	6.0 kJ/m ²	ISO 180/1A
23°C ⁸	10 kJ/m ²	ISO 180/1A
Unnotched Izod Impact (23°C)	640 J/m	ASTM D4812
Instrumented Dart Impact		ASTM D3763
23°C, Energy at Peak	5.00 J	
23°C, Total Energy	17.0 J	
Hardness	Nominal Value Unit	Test Method
Rockwell Hardness (R-Scale)	109	ASTM D785
Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load		
0.45 MPa, Unannealed, 6.40 mm	204 °C	ASTM D648
1.8 MPa, Unannealed, 3.20 mm	163 °C	ASTM D648
1.8 MPa, Unannealed, 6.40 mm	149 °C	ASTM D648
1.8 MPa, Unannealed, 4.00 mm, 64.0 mm Span ⁸	155 °C	ISO 75-2/Af
Vicat Softening Temperature		
--	153 °C	ASTM D1525 ⁹
--	150 °C	ISO 306/B120
--	148 °C	ISO 306/B50
CLTE		
Flow : -40 to 40°C	2.7E-5 cm/cm/°C	ASTM E831 ISO 11359-2
Flow : 60 to 138°C	2.0E-5 cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	1.1E-4 cm/cm/°C	ASTM E831 ISO 11359-2
RTI Elec	140 °C	UL 746B
RTI Imp	130 °C	UL 746B
RTI Str	140 °C	UL 746B
Electrical	Nominal Value Unit	Test Method
Volume Resistivity	4.8E+15 ohms·cm	ASTM D257
Dielectric Strength		ASTM D149
1.60 mm, in Oil	27 kV/mm	
3.20 mm, in Air	20 kV/mm	
Dielectric Constant		ASTM D150
100 Hz	4.00	
1 MHz	4.00	
Dissipation Factor		ASTM D150
100 Hz	3.0E-3	
1 MHz	0.020	
Arc Resistance ¹⁰	PLC 5	ASTM D495
Comparative Tracking Index (CTI)	PLC 2	UL 746A
High Amp Arc Ignition (HAI) ¹¹	PLC 3	UL 746A
High Voltage Arc Resistance to Ignition (HVAR)	PLC 1	UL 746A
Hot-wire Ignition (HWI)	PLC 1	UL 746A



XENOV™ Resin 6370 - Asia

Polycarbonate + PBT

SABIC

PROSPECTOR®

www.ulprospector.com

Flammability	Nominal Value Unit	Test Method
Flame Rating (1.5 mm)	HB	UL 94

Injection	Nominal Value Unit
Drying Temperature	110 °C
Drying Time	4.0 to 6.0 hr
Suggested Max Moisture	0.020 %
Suggested Shot Size	50 to 80 %
Rear Temperature	250 to 270 °C
Middle Temperature	255 to 275 °C
Front Temperature	260 to 280 °C
Nozzle Temperature	255 to 275 °C
Processing (Melt) Temp	260 to 280 °C
Mold Temperature	65 to 95 °C
Back Pressure	0.300 to 0.600 MPa
Screw Speed	50 to 80 rpm
Vent Depth	0.013 to 0.020 mm

Injection Notes

- Drying Time (Cumulative): 8 hr

Notes

¹ Typical properties: these are not to be construed as specifications.

² 5.0 mm/min

³ Type I, 5.0 mm/min

⁴ 1.3 mm/min

⁵ 2.0 mm/min

⁶ at Yield

⁷ 80*10*4 sp=62mm

⁸ 80*10*4 mm

⁹ Rate A (50°C/h), Loading 2 (50 N)

¹⁰ Tungsten Electrode

¹¹ Surface



XENOY™ Resin 6370 - Asia

Polycarbonate + PBT

SABIC

PROSPECTOR®

www.ulprospector.com

Where to Buy

Supplier

SABIC

Web: <http://www.sabic.com/>

Distributor

3Polymer (Guangzhou) Chemical Technology Co., Ltd.

Telephone: +86-20-3466-7988

Web: <http://3polymer.com>

Availability: China

