

STARESTER™ PBT 1100A

PBT 1100A is a general purpose grade base resin, with non-reinforced, medium viscosity, which can be used in injection molding.

聚对苯二甲酸丁二醇酯（PBT 1100A）通用级基础树脂，中等粘度，注塑级。

TYPICAL PROPERTIES 典型性能	TYPICAL VALUE 典型值	UNIT 单位	STANDARD 参考标准
PHYSICAL PROPERTIES/物理性能			
Density 密度	1.31±0.02	g/cm ³	ASTM D792
Intrinsic Viscosity 特性粘度	1.050±0.020	dl/g	ASTM D445
Melting temperature 熔点	224.0±2.0	°C	ISO 11357, DSC Way
Melt Flow Rate, 235°C/2.16kg 熔体流动速率, 235°C/2.16kg	16.0-20.0	g/10min	ASTM D1238
Melt Flow Rate, 250°C/2.16kg 熔体流动速率, 250°C/2.16kg	25.0-35.0	g/10min	ASTM D1238
Melt Flow Rate, 250°C/5.00kg 熔体流动速率, 250°C/5.00kg	58.0-68.0	g/10min	ASTM D1238
CEG(Carboxyl End Groups) 端羧基含量	≤30	meq/kg	Potentiometric titration 电位滴定法
Color b 色泽b值	≤5.0	Hunter Lab Photometer	(D65,10°)
Color L 色泽L值	≥91.0		(D65,10°)
Ash Content 灰分	≤0.035	%	ASTMD5630-06
Moisture Content 含水率	≤0.30	%	ASTM D570
Chip Powder Content 切粉量	≤50	PPM	GB T9345.1-2008
Chip Size 百粒重	2.0±0.2	G	Bluestar Internal Standard 蓝星内部测试方法
MECHANICAL/机械性能			
Tensile Strength (50mm/min) 拉伸强度 (50mm/min)	50-60	MPa	ASTM D638
Tensile Elongation 断裂伸长率	≥100	%	ASTM D638
Flexible Strength 弯曲强度	≥75	MPa	ASTM D790
Izod Impact, notched, 23°C 悬臂梁缺口冲击, 23°C	≥4.0	KJ/M ²	ASTM D256
THERMAL PROPERTIES/热性能			
HDT, 1.80MPa, 3.2mm 热变形温度, 1.80MPa, 3.2mm	55	°C	ASTM D648

Disclaimer/免责声明

All figures in the table are the typical values of the material and not the minimum values of the material specifications.

以上表格中的所有数值均为典型值，非标准值。

All data shown here are not always applicable to parts used under different conditions. We do not guarantee that these data are directly applicable to the application conditions of users and we ask each user to make his own decision on the application.

以上数据可能会因为条件不同而不同，我们无法保证以上数据对应于客户所使用的条件，建议客户使用时注意此项。

For safe handling of materials we supply, it is advised to refer to the Material Safety Data Sheet "MSDS" of the proper material.

我们所供材料的安全使用方面，请适当参阅材料安全数据表“MSDS”。

STARESTER™ PBT 1100A

PROCESSING PARAMETERS 工艺参数	TYPICAL VALUE 典型值	UNIT 单位
INJECTION MOLDING/ 注塑成型加工		
Drying Temperature 干燥温度	120-140	℃
Drying Time 干燥时间	3-4	hrs
Melt Temperature 熔体温度	235-250	℃
Nozzle Temperature 射嘴温度	240	℃
Mold Temperature 模具温度	60-80	℃
Injection Pressure 注射压力	40-100	MPa
Back Pressure 背压	4-15	MPa
Screw Speed 螺杆速度	<100	RPM

• NOTE: Injection Pressure, Back Pressure and Screw Speed are only mentioned as general guidelines. These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.
注：注射压力、背压和螺杆速度等条件及其设置与制件大小、厚度、模具有关，以上仅作参考。

COMPOUNDING EXTRUSION /改性挤出成型加工		
Drying Temperature 干燥温度	120-140	℃
Drying Time 干燥时间	3-4	H/小时
Melt Temperature 熔体温度	220-250	℃
Extruder Temperature ZONE1, close to feeder 螺杆一区温度（靠近喂料口）	210-245	℃
Extruder Temperature ZONE2 螺杆二区温度	210-245	℃
Extruder Temperature ZONE3 螺杆三区温度	210-245	℃
Extruder Temperature ZONE4 螺杆四区温度	210-245	℃
Extruder Temperature ZONE5, close to die 螺杆五区温度（靠近口模）	210-245	℃
Screw Speed 螺杆速度	≤900	RPM

Contact Information/ 联系方式

企业名称：南通星辰合成材料有限公司
联系地址：江苏省南通市经济技术开发区江港路118号
联系电话：+86-0513-85997855（全球市场）
+86-0513-85997877（国内市场，大客户经理）
+86-0513-85997886（国内市场，华东片区）
+86-0513-85997889（国内市场，华南片区）
+86-0513-85997898（电商平台销售）
公司网站：<http://www.ntsmp.com>
电子邮件：PBT@bluestar.chemchina.com

Company: Nantong Xingchen Synthetic Material Co., Ltd.
Address: 118, Jianggang Rd, Nantong Economic Development Zone, Jiangsu Province, PRC, China.
(Postcode: 226017)
Telephone: +86-0513-85997855 Global Market
+86-0513-85997877 Key Account Customer China
+86-0513-85997886 East China Market
+86-0513-85997889 South China Market
+86-0513-85997898 E-commerce Platform
Website: <http://www.ntsmp.com>
Email: PBT@bluestar.chemchina.com

