

DENYL 66 3010

Polyamide 66

Vamp Tech

PROSPECTOR®

www.ulprospector.com

Technical Data

Product Description

PA66 resin 30% glass fiber reinforced for injection moulding

General

Material Status • Commercial: Active

Search for UL Yellow Card • Vamp Tech

Availability • Africa & Middle East • Europe • North America
• Asia Pacific • Latin America

Filler / Reinforcement • Glass Fiber, 30% Filler by Weight

Processing Method • Injection Molding

Physical	Nominal Value Unit	Test Method
Density	1.36 g/cm ³	ISO 1183
Molding Shrinkage		ASTM D955
Flow	0.50 %	
Across Flow	0.90 %	

Mechanical	Nominal Value Unit	Test Method
Tensile Modulus	9000 MPa	ISO 527-1
Tensile Stress (Break)	170 MPa	ISO 527-2
Tensile Strain (Break)	3.5 %	ISO 527-2

Impact	Nominal Value Unit	Test Method
Notched Izod Impact Strength	10 kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	70 kJ/m ²	ISO 180

Thermal	Nominal Value Unit	Test Method
Deflection Temperature Under Load		ASTM D648
1.8 MPa, Unannealed	250 °C	
Continuous Use Temperature	140 °C	
Vicat Softening Temperature	250 °C	ASTM D1525 ²

Injection	Nominal Value Unit
Drying Temperature	90 °C
Drying Time	3.0 hr
Processing (Melt) Temp	280 °C
Mold Temperature	100 °C

Notes

¹ Typical properties: these are not to be construed as specifications.

² Loading 2 (50 N)



DENYL 66 3010

Polyamide 66

Vamp Tech

PROSPECTOR®

www.ulprospector.com

Where to Buy

Supplier

Vamp Tech

Busnago, Busnago Italy

Telephone: +39-39-695-7821

Web: <http://www.vamptech.com/>

Distributor

Biesterfeld Plastic GmbH

Biesterfeld is a Pan European distribution company. Contact Biesterfeld for availability of individual products by country.

Telephone: +49-40-32-00-80

Web: <https://www.biesterfeld.com/>

Availability: Asia Pacific

Omya Specialty Materials Inc.

Telephone: Customer Service: (800) 937-3877; Sales & Product Management: +1-470-677-8945

Web: https://distribution-us.omya.com/?utm_source=ul-prospector&utm_medium=affiliate&utm_campaign=bu:material-science---construction~cc:ram~cn:ul-prospector_material_sciences~co:lg~ff:&utm_content=navlink

Availability: North America

