

# VAMPAMID HT 3028 V0

Polyphthalamide

Vamp Tech

PROSPECTOR®

www.ulprospector.com

## Technical Data

### Product Description

PPA resin, 30% glass fiber reinforced, flame retarded halogen free for injection moulding

### General

|                             |                                            |                             |                 |
|-----------------------------|--------------------------------------------|-----------------------------|-----------------|
| Material Status             | • Commercial: Active                       |                             |                 |
| UL Yellow Card <sup>1</sup> | • E140692-104409674<br>• E140692-104409676 |                             |                 |
| Search for UL Yellow Card   | • Vamp Tech<br>• VAMPAMID                  |                             |                 |
| Availability                | • Africa & Middle East<br>• Asia Pacific   | • Europe<br>• Latin America | • North America |
| Filler / Reinforcement      | • Glass Fiber, 30% Filler by Weight        |                             |                 |
| Features                    | • Flame Retardant                          | • Halogen Free              |                 |
| Processing Method           | • Injection Molding                        |                             |                 |

| Physical                                                 | Nominal Value Unit     | Test Method    |
|----------------------------------------------------------|------------------------|----------------|
| Density                                                  | 1.44 g/cm <sup>3</sup> | ISO 1183       |
| Molding Shrinkage                                        |                        | ASTM D955      |
| Flow                                                     | 0.30 %                 |                |
| Across Flow                                              | 0.70 %                 |                |
| Water Absorption (24 hr, 23°C)                           | 0.40 %                 | ASTM D570      |
| Mechanical                                               | Nominal Value Unit     | Test Method    |
| Tensile Modulus                                          | 11500 MPa              | ISO 527-1      |
| Tensile Stress (Break)                                   | 160 MPa                | ISO 527-2      |
| Tensile Strain (Break)                                   | 2.0 %                  | ISO 527-2      |
| Impact                                                   | Nominal Value Unit     | Test Method    |
| Notched Izod Impact Strength                             | 7.0 kJ/m <sup>2</sup>  | ISO 180/A      |
| Unnotched Izod Impact Strength                           | 50 kJ/m <sup>2</sup>   | ISO 180        |
| Thermal                                                  | Nominal Value Unit     | Test Method    |
| Deflection Temperature Under Load<br>1.8 MPa, Unannealed | 270 °C                 | ASTM D648      |
| Ball Pressure Test (> 200°C)                             | Pass                   | IEC 60695-10-2 |
| RTI Elec                                                 | 155 °C                 | UL 746B        |
| RTI Imp                                                  | 125 °C                 | UL 746B        |
| RTI Str                                                  | 130 °C                 | UL 746B        |
| Electrical                                               | Nominal Value Unit     | Test Method    |
| Surface Resistivity                                      | > 1.0E+12 ohms         | ASTM D257      |
| Electric Strength                                        | 36 kV/mm               | IEC 60243-1    |
| Comparative Tracking Index                               | 600 V                  | IEC 60112      |
| Flammability                                             | Nominal Value Unit     | Test Method    |
| Flame Rating                                             |                        | UL 94          |
| 0.40 mm                                                  | V-0                    |                |
| 0.8 mm                                                   | V-0                    |                |
| 1.6 mm                                                   | V-0                    |                |
| 3.2 mm                                                   | V-0                    |                |
| Glow Wire Flammability Index (1.0 to 2.0 mm)             | 960 °C                 | IEC 60695-2-12 |
| Glow Wire Ignition Temperature<br>1.0 to 2.0 mm          | 775 °C                 | IEC 60695-2-13 |



VAMPAMID HT 3028 V0

Polyphthalamide

Vamp Tech

PROSPECTOR®

www.ulprospector.com

| Injection              | Nominal Value Unit |
|------------------------|--------------------|
| Drying Temperature     | 90 °C              |
| Drying Time            | 3.0 hr             |
| Processing (Melt) Temp | 320 °C             |
| Mold Temperature       | 130 °C             |

Notes

<sup>1</sup> A UL Yellow Card contains UL-verified flammability and electrical characteristics. UL Prospector continually works to link Yellow Cards to individual plastic materials in Prospector, however this list may not include all of the appropriate links. It is important that you verify the association between these Yellow Cards and the plastic material found in Prospector. For a complete listing of Yellow Cards, visit the UL Yellow Card Search.

<sup>2</sup> Typical properties: these are not to be construed as specifications.



## VAMPAMID HT 3028 V0

Polyphthalamide

**Vamp Tech**

**PROSPECTOR®**

[www.ulprospector.com](http://www.ulprospector.com)

### Where to Buy

#### Supplier

##### **Vamp Tech**

Busnago, Busnago Italy

**Telephone:** +39-39-695-7821

**Web:** <http://www.vamptech.com/>

#### Distributor

##### **ALBIS**

*ALBIS is a global distribution company. Contact ALBIS for availability of individual products per country.*

**Telephone:** +49-40-78105-0

**Web:** <https://www.albis.com/albis-distribution/en/about/locations>

**Availability:** Algeria, Austria, Belgium, Czech Republic, Germany, Hungary, Luxembourg, Morocco, Netherlands, Poland, Tunisia

