

SELCION[®] KD130Ni(Bi)

SELCION[®] LCP KD130Ni(Bi) is a 30% glass fiber reinforced LCP for general purpose with high flowability.

性能	PROPERTIES	典型数值	VALUE	单位	UNIT	测试标准	TEST METHOD
机械性能 MECHANICAL							
拉伸强度	Tensile Strength@break	137		MPa		ASTM D638	
断裂伸长率	Tensile Elongation@break	2.1		%		ASTM D638	
弯曲强度	Flexural Strength	190		MPa		ASTM D790	
弯曲模量	Flexural Modulus	12		GPa		ASTM D790	
IZOD 无缺口冲击强度	IZOD un-notched impact strength	460		J/m			
热性能 THERMAL							
热变形温度	Heat distortion temperature 18.5kgf/cm ²	276		°C		ASTM D648	
物理性能 PHYSICAL							
比重	Specific Gravity	1.62				ASTM D792	
成型收缩率	MD / TD at 2mmt	0.08 / 0.61		%		In house	
烤炉起泡	270°C, 10min	OK				In house	
难燃性能	Flame Retardancy	V-0 (0.3 mmt)				UL-94	

加工性能	PROCESSING CONDITIONS	典型数值	VALUE	单位	UNIT	备注	REMARK
射嘴温度	Nozzle Temp.	325-345		°C		335 is recommended	
前段温度	Front Temp.	335-355		°C		345 is recommended	
中段温度	Middle Temp.	325-345		°C		335 is recommended	
后段温度	Rear Temp.	300-320		°C		310 is recommended	
加料口温度	Feed zone Temp.	50-70		°C		60 is recommended	
模具温度	Mold Temp.	80-120		°C		100 is recommended	
干燥温度	Drying Temperature	140-160		°C		150 is recommended	
干燥时间	Drying Time	4-8		h		6 Hr is recommended	

※ 成型条件根据不同的機種和操作环境而不同

