

产品物性表    Technical Data

PC/ASA 3026-AS

- ✧ 主要特征： PC/ASA 合金，耐候性优异，注塑应用。
- ✧ Product Description: PC/ASA Alloy, Excellent Weatherability, Injection Molding.

| 性能<br>Properties                              | 测试条件<br>Test Condition | 典型值<br>Typical Value | 国际单位<br>Unit | 测试标准<br>Test Standard |
|-----------------------------------------------|------------------------|----------------------|--------------|-----------------------|
| 机械性能 Mechanical                               |                        |                      |              |                       |
| 拉伸强度 Tensile Strength                         | 50mm/min               | 55                   | MPa          | ASTM D638             |
| 断裂伸长率 Tensile Strain at Break                 | 50mm/min               | 100                  | %            | ASTM D638             |
| 弯曲模量 Flexural Strength                        | 5mm/min                | 2200                 | MPa          | ASTM D790             |
| 弯曲强度 Flexural Modulus                         | 5mm/min                | 85                   | MPa          | ASTM D790             |
| 悬臂梁缺口冲击(23℃)<br>Izod Notched Impact Strength  | 3.18mm                 | 680                  | J/m          | ASTM D256             |
| 物理性能 Physical                                 |                        |                      |              |                       |
| 比重 Density                                    | 23℃                    | 1.15                 | g/cm³        | ASTM D792             |
| 熔指 Melt Flow Index                            | 260℃, 5kg              | 22                   | g/10min      | ASTM D1238            |
| 收缩率 Molding Shrinkage                         | -                      | 0.5-0.7              | %            | ASTM D955             |
| 阻燃性能 Flammability                             |                        |                      |              |                       |
| 阻燃等级 Flame Rating                             | 1.5mm                  | HB                   | -            | UL 94                 |
| 热性能 Thermal                                   |                        |                      |              |                       |
| 热变形温度<br>Temperature of Deflection Under Load | 1.8MPa                 | 100                  | ℃            | ASTM D648             |

## 典型加工条件 Typical Processing Conditions

|                           | 典型范围 Range (Optimum) | 单位 unit |
|---------------------------|----------------------|---------|
| 预干燥温度 Pre-dry Temperature | 90-110               | °C      |
| 预干燥时间 Pre-dry Time        | 2-4                  | hrs     |
| 熔体温度 Melt Temperature     | 260-280              | °C      |
| 料筒后段温度 Rear Temperature   | 240-250              | °C      |
| 料筒中段温度 Middle Temperature | 250-270              | °C      |
| 料筒前段温度 Front Temperature  | 260-280              | °C      |
| 模温 Mold Temperature       | 60-100               | °C      |

\*数据为实验典型值，只作为客户使用的参考，不作为质保承诺。

不同的颜色性能可能会不同。

\*These are typical values of the product's properties, and these values alone do not represent a sufficient basis for any part design and are not intended for use in not the permit of quality assurance

The listed values are maybe different for pigmented material.

## 安全及处理注意事项 Safety & Handling Considerations

### 急救措施

若吸入熔融树脂逸出之气体，将患者移至通风处，立即送医。若接触到熔胶，以大量（肥皂）水冲洗患处及衣物，立即送医。若接触到塑胶粒或塑胶粉末，以大量清水至少冲洗 15 分钟，若有不适，立即送医。若接触到高温熔融树脂逸出之气体，以大量清水至少冲洗 15 分钟，若有不适，立即送医。不慎吞食请催吐，以清水漱口，若有不适，立即送医。

### FIRST AID MEASURES

Once inhaling of evaporated gas when the resin is melted, move subject to open space and seek medical advice immediately. Once contact with pellets or powder, flush with clean water for 15 min. Once contact with molten resin, flush with suds for 15 min and seek medical advice immediately. Seek medical advice immediately if any discomfortableness remains. Once swallowing accidentally, induce vomiting and rinse mouth with clean water. Seek medical advice if necessary.

### 安全处置与储存方法

处置操作处所须严禁烟火，做好整理整顿以避免粉尘累积。为防止尘爆，空气输送管路，袋滤器及储槽须加装静电消除装置，并确实接地。袋滤器之滤材采导电性材质。储存存放于阴凉处所，避免直射阳光，雨淋及急速之温差。储存处严禁烟火。

### HANDLING AND STORAGE

Prohibit open fire and concentration of dust or powder in processing site and warehouse. To avoid dust explosion resulting from the existence of powder, electrostatics eliminators and grounding should be equipped to air transferring pipes, bag filters and hoppers. Additionally, use electrically conductive filters for bag filters. Store the goods in a cool and dry place. Protect from direct sunlight, rain and violent temperature fluctuation. Fire is inhibited around storage area.