

LUMID GP2300BAH

Injection Molding, PA 66+GF30% , Good appearance

Description

Injection grade

Application

Electric parts

Properties	Test Condition	Test Method	Unit	Typical Value
Physical				
Specific Gravity		ASTM D792	-	1.37
Molding Shrinkage (Flow), 3.2mm		ASTM D955	%	0.4~0.9
Melt Flow Rate		ASTM D1238	g/10min	
Water Absorption	23°C, 24hrs	ASTM D570	%	1.1
Mechanical				
Tensile Strength, 3.2mm		ASTM D638		
@ Break	5mm/min		kg/cm ²	1,700
Tensile Elongation, 3.2mm		ASTM D638		
@ Break	5mm/min		%	5
Flexural Strength, 3.2mm	1.3mm/min	ASTM D790	kg/cm ²	2,500
Flexural Modulus, 3.2mm	1.3mm/min	ASTM D790	kg/cm ²	75,000
IZOD Impact Strength, 3.2mm		ASTM D256		
(Notched)	23°C		kg·cm/cm	8
	-30°C		kg·cm/cm	
Rockwell Hardness	R-Scale	ASTM D785	-	
Thermal				
Heat Deflection Temperature, 6.4mm		ASTM D648		
(Unannealed)	18.6kg		°C	243
	4.6kg		°C	
Melting Temperature		ASTM D3418	°C	
Flammability		UL94		
0.75mm			class	HB
1.5mm			class	HB
3.0mm			class	HB
Relative Temperature Index		UL 746B		
Electrical			°C	120
Mechanical with Impact			°C	110
Mechanical without Impact			°C	120

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection molded specimens and after 48 hours storage at 23°C, 50% relative humidity.

Updated : Mar-20, 2015

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

LUMID GP2300BAH

Injection Molding, PA 66+GF30% , Good appearance

Description

Injection grade

Application

Electric parts

Electrical

Comparative Tracking Index(CTI)	Solution A	IEC 60112	Volts	
Volume Resistivity	23℃	ASTM D257	Ohm·m	1.0E+14
Arc Resistance	23℃	ASTM D495	Ohm·cm	
Dielectric Strength, 1mm	23℃	ASTM D149	kV/mm	25
Dielectric Constant (10 ⁶ Hz)	23℃	ASTM D150	sec	4

Note) Typical values are only for material selection purpose, and variation within normal tolerances are for various colors.

Values given should not be interpreted as specification and not be used for part or tool design.

All properties, except melt flow rate are measured on injection molded specimens and after 48 hours storage at 23℃, 50% relative humidity.

Processing Guide (Extrusion Molding)

Processing Parameters		Unit	Value
Drying Temperature		℃	80~100
Drying Time		hrs	4~5
Maximum Moisture Content		%	0.12
Melt Temperature		℃	270~290
Barrel Temperature	Rear	℃	265~275
	Middle	℃	270~285
	Front	℃	270~290
Die Temperature		℃	270~295
Mold Temperature		℃	80~110
Back Pressure	Hydraulic Type	kg/cm ²	10~30
Screw Speed		rpm	60~150

Note) Back Pressure & Screw Speed are only mentioned as general guidelines.

These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

Updated : Mar-20, 2015

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.