



Bayblend T70 X

Preliminary Product Description

Standard grades

(PC+ABS) Blend; Vicat B120 = 123°C; good injection molding processing behaviour (easy flowing), excellent long-term ageing behaviour under humid conditions and painting performance; good chemical resistance: low VOC emissions & odour

Property	Test Condition	Unit	Standard	Typical Value*
Rheological Properties				
Melt Viscosity	260 °C; 1000 s ⁻¹	Pa·s	b.o. ISO 11443-A	210
Melt Viscosity	280 °C; 1000 s ⁻¹	Pa·s	b.o. ISO 11443-A	155
Melt volume-flow rate (MVR)	260 °C / 5 kg	cm ³ /10 min	ISO 1133	18
Molding shrinkage, parallel	60x60x2; 500 bar	%	b.o. ISO 2577	0.55 - 0.75
Molding shrinkage, normal	60x60x2; 500 bar	%	b.o. ISO 2577	0.55 - 0.75

Mechanical properties (23 °C, 50 % r. F.)

Tensile modulus	1 mm/min	MPa	ISO 527-1,-2	2300
Yield stress	5 mm/min	MPa	ISO 527-1,-2	54
Yield strain	5 mm/min	%	ISO 527-1,-2	4.7
Stress at break	5 mm/min	MPa	ISO 527-1,-2	50
Strain at break	5 mm/min	%	ISO 527-1,-2	110
Charpy impact strength	23 °C	kJ/m ²	ISO 179-1eU	no break
Charpy impact strength	-30 °C	kJ/m ²	ISO 179-1eU	no break
Izod impact strength	23 °C	kJ/m ²	ISO 180/U	no break
Izod impact strength	-30 °C	kJ/m ²	ISO 180/U	no break
Charpy notched impact strength	23 °C	kJ/m ²	ISO 179-1eA	65
Charpy notched impact strength	-30 °C	kJ/m ²	ISO 179-1eA	55
Izod notched impact strength	23 °C	kJ/m ²	ISO 180/A	53
Izod notched impact strength	-30 °C	kJ/m ²	ISO 180/A	44
Puncture maximum force	23 °C; 2 mm	N	ISO 6603-2	4300
Puncture maximum force	-30 °C; 2 mm	N	ISO 6603-2	5300
Puncture energy	23 °C; 2 mm	J	ISO 6603-2	48
Puncture energy	-30 °C; 2 mm	J	ISO 6603-2	54

Thermal properties

Temperature of deflection under load	1.80 MPa	°C	ISO 75-1,-2	103
Temperature of deflection under load	0.45 MPa	°C	ISO 75-1,-2	125
Vicat softening temperature	50 N; 50 °C/h	°C	ISO 306	121
Vicat softening temperature	50 N; 120 °C/h	°C	ISO 306	123
Coefficient of linear thermal exp., parallel	23-55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.7
Coefficient of linear thermal exp., transverse	23-55 °C	10 ⁻⁴ /K	ISO 11359-1,-2	0.7
Burning behavior UL 94	0.85 mm	Class	UL 94	HB (internal test)

Electrical properties (23 °C, 50 % r. h.)

Volume resistivity		Ohm·m	IEC 60093	1E16
Surface resistivity		Ohm	IEC 60093	1E16

Other properties (23 °C)

Density		kg/m ³	ISO 1183	1130
---------	--	-------------------	----------	------

Recommended Processing and Drying Conditions**

Melt Temperatures		°C		270 - 290
Standard Melt Temperature		°C		280
Mold Temperatures		°C		70 - 90
Dry Air Drying Temperature		°C		95 - 110
Dry Air Drying Time		h		4
Moisture Content max. (%)		%		0.01



Bayblend T70 X

Disclaimer

*Typical value

These values are typical values only. Unless explicitly agreed in written form, they do not constitute a binding material specification or warranted values. Values may be affected by the design of the mold/die, the processing conditions and coloring/pigmentation of the product. Unless specified to the contrary, the property values given have been established on standardized test specimens at room temperature.

**Recommended Processing and Drying Conditions

Drying conditions are for dry air dryers only. Drying times and drying temperatures may differ depending on valid dryer type. Further information is provided by your local Covestro support.

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by Covestro.

Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.