

# Akulon® S223-KG6

## PA66-GF30

Glass Reinforced, Heat Stabilized

Print Date: 2021-02-13

| Properties                                   | Typical Data | Unit              | Test Method    |
|----------------------------------------------|--------------|-------------------|----------------|
| <b>Rheological properties</b>                |              |                   |                |
|                                              | dry / cond   |                   |                |
| Molding shrinkage (parallel)                 | 0.2 / *      | %                 | ISO 294-4      |
| Molding shrinkage (normal)                   | 1 / *        | %                 | ISO 294-4      |
| <b>Mechanical properties</b>                 |              |                   |                |
|                                              | dry / cond   |                   |                |
| Tensile modulus                              | 9500 / 7500  | MPa               | ISO 527-1/-2   |
| Stress at break                              | 190 / 140    | MPa               | ISO 527-1/-2   |
| Strain at break                              | 3 / 5        | %                 | ISO 527-1/-2   |
| Flexural modulus                             | 8400 / -     | MPa               | ISO 178        |
| Flexural strength                            | 250 / -      | MPa               | ISO 178        |
| Charpy impact strength (+23°C)               | 80 / 100     | kJ/m <sup>2</sup> | ISO 179/1eU    |
| Charpy impact strength (-30°C)               | 70 / 70      | kJ/m <sup>2</sup> | ISO 179/1eU    |
| Charpy notched impact strength (+23°C)       | 12 / 20      | kJ/m <sup>2</sup> | ISO 179/1eA    |
| Charpy notched impact strength (-30°C)       | 10 / 10      | kJ/m <sup>2</sup> | ISO 179/1eA    |
| <b>Thermal properties</b>                    |              |                   |                |
|                                              | dry / cond   |                   |                |
| Melting temperature (10°C/min)               | 260 / *      | °C                | ISO 11357-1/-3 |
| Temp. of deflection under load (1.80 MPa)    | 245 / *      | °C                | ISO 75-1/-2    |
| Temp. of deflection under load (0.45 MPa)    | 260 / *      | °C                | ISO 75-1/-2    |
| Coeff. of linear therm. expansion (parallel) | 0.2 / *      | E-4/°C            | ISO 11359-1/-2 |
| Coeff. of linear therm. expansion (normal)   | 0.7 / *      | E-4/°C            | ISO 11359-1/-2 |
| <b>Other properties</b>                      |              |                   |                |
|                                              | dry / cond   |                   |                |
| Water absorption                             | 6 / *        | %                 | Sim. to ISO 62 |

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. This document replaces all previous versions relating to this subject.

Copyright © DSM 2021. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.

## Property Data

# Akulon<sup>®</sup> S223-KG6

Print Date: 2021-02-13

| Properties          | Typical Data | Unit              | Test Method    |
|---------------------|--------------|-------------------|----------------|
| Humidity absorption | 1.6 / *      | %                 | Sim. to ISO 62 |
| Density             | 1360 / -     | kg/m <sup>3</sup> | ISO 1183       |

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. This document replaces all previous versions relating to this subject.

Copyright © DSM 2021. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.