

Stanyl® HFX31SW

PA46-GF20 FR(40)

20% Glass Reinforced, High Flow, Halogen free and free of red phosphorous

Print Date: 2017-11-08

Properties	Typical Data	Unit	Test Method
Mechanical properties			
	dry / cond		
Tensile modulus	8200 / -	MPa	ISO 527-1/-2
Stress at break	110 / -	MPa	ISO 527-1/-2
Strain at break	2.6 / -	%	ISO 527-1/-2
Flexural modulus	8000 / -	MPa	ISO 178
Charpy notched impact strength (+23°C)	5.5 / -	kJ/m ²	ISO 179/1eA
Thermal properties			
	dry / cond		
Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	285 / *	°C	ISO 75-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	IEC 60695-11-10
Burning Behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.2 / *	mm	IEC 60695-11-10
Other properties			
	dry / cond		
Density	1470 / -	kg/m ³	ISO 1183

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. This document replaces all previous versions relating to this subject.

Copyright © DSM 2017. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.



DSM

BRIGHT SCIENCE. BRIGHTER LIVING.