

Xytron™ C66379B

PPS-MD

Print Date: 2023-08-02

Properties	Typical Data	Unit	Test Method
Mechanical properties			
	Value		
Tensile modulus	8900	MPa	ISO 527-1/-2
Stress at break	71	MPa	ISO 527-1/-2
Strain at break	1	%	ISO 527-1/-2
Izod impact strength (+23°C)	28	kJ/m ²	ISO 180/1U
Izod notched impact strength (+23°C)	5.2	kJ/m ²	ISO 180/1A
Thermal properties			
	Value		
Burning Behav. at 0.75 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	0.8	mm	IEC 60695-11-10
Electrical properties			
	Value		
Relative permittivity (5GHz)	8.7	-	IEC 61189-2-721
Dissipation factor (5GHz)	24	E-4	IEC 61189-2-721

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl®, UDea™ and Xytron™ are trademarks of Envalior. Seller represents and warrants exclusively that on the date of delivery by Seller the product shall be in conformity with the specifications agreed upon. Seller makes no other representations or warranties, whether express or implied.

Seller is not responsible or liable for the design of the products of the Customer and it is the responsibility of the Customer to determine that the Seller's product is safe, complies with application laws and regulations, and is technically or otherwise fit for its intended use. Seller does not endorse or claim suitability of its products for a specific application and disclaims each and every representation or warranty, whether express or implied, in that respect.

Typical values are indicative only and are not to be construed as being binding specifications. Colorants in the product or other additives may cause significant variations in typical values. This document replaces all previous versions relating to this subject.

Copyright © Envalior 2023. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of Envalior.

