

Xytron™ M6510A

PPS-(GF+MD)65

65% Glass/Mineral Reinforced, Flame Retardant, Excellent Dimensional Stability

Print Date: 2020-05-07

Properties	Typical Data	Unit	Test Method
Rheological properties			
	Value		
Molding shrinkage (parallel)	0.3	%	ISO 294-4
Molding shrinkage (normal)	0.5	%	ISO 294-4
Mechanical properties			
	Value		
Tensile modulus	20000	MPa	ISO 527-1/-2
Tensile modulus (120°C)	11000	MPa	ISO 527-1/-2
Tensile modulus (160°C)	8900	MPa	ISO 527-1/-2
Tensile modulus (180°C)	8000	MPa	ISO 527-1/-2
Tensile modulus (200°C)	7700	MPa	ISO 527-1/-2
Stress at break	145	MPa	ISO 527-1/-2
Stress at break (120°C)	98	MPa	ISO 527-1/-2
Stress at break (160°C)	75	MPa	ISO 527-1/-2
Stress at break (180°C)	70	MPa	ISO 527-1/-2
Stress at break (200°C)	62	MPa	ISO 527-1/-2
Strain at break	1	%	ISO 527-1/-2
Strain at break (120°C)	1.7	%	ISO 527-1/-2
Strain at break (160°C)	2.4	%	ISO 527-1/-2
Strain at break (180°C)	2.5	%	ISO 527-1/-2
Strain at break (200°C)	2.5	%	ISO 527-1/-2
Flexural modulus	20000	MPa	ISO 178
Flexural strength	230	MPa	ISO 178
Flexural modulus (120°C)	14000	MPa	ISO 178
Flexural modulus (160°C)	9100	MPa	ISO 178

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. This document replaces all previous versions relating to this subject.

Copyright © DSM 2020. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.



DSM

BRIGHT SCIENCE. BRIGHTER LIVING.

Xytron™ M6510A

Print Date: 2020-05-07

Properties	Typical Data	Unit	Test Method
Flexural modulus (200°C)	7000	MPa	ISO 178
Charpy impact strength (+23°C)	25	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	27	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	6.5	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	6.8	kJ/m ²	ISO 179/1eA
Rockwell hardness, R scale	120	-	ISO 2039-2
Rockwell hardness, M scale	101	-	ISO 2039-2

Thermal properties

Value

Melting temperature (10°C/min)	280	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	277	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.15	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.27	E-4/°C	ISO 11359-1/-2
Coef. of lin. therm expansion, parallel, above Tg	0.15	E-4/°C	ISO 11359-1/-2
Coef. of lin. therm expansion, normal, above Tg	0.75	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.5	mm	IEC 60695-11-10
UL recognition	Yes	-	-
Burning Behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.7	mm	IEC 60695-11-10
UL recognition	Yes	-	-
Relative Temperature Index - electrical	130	°C	UL746B
RTI electrical (Thickness (1) tested)	0.7	mm	UL746B

Electrical properties

Value

Volume resistivity	>1E13	Ohm*m	IEC 60093
Electric strength	25	kV/mm	IEC 60243-1
Comparative tracking index	225	V	IEC 60112
Dissipation factor (5GHz)	44	E-4	IEC 60250
Relative permittivity (5GHz)	5	-	IEC 60250

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. This document replaces all previous versions relating to this subject.

Copyright © DSM 2020. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.

Xytron™ M6510A

Print Date: 2020-05-07

Properties	Typical Data	Unit	Test Method
Other properties	Value		
Density	1970	kg/m ³	ISO 1183

Akulon®, Arnite®, Arnitel®, EcoPaXX®, ForTii®, Novamid®, Stanyl® and Xytron™ are trademarks of DSM.

All information supplied by or on behalf of DSM in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but DSM assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information, or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequences from the use of all such information.

Typical values are indicative only and are not to be construed as being binding specifications. This document replaces all previous versions relating to this subject.

Copyright © DSM 2020. All rights reserved. No part of the information may be reproduced, distributed, or transmitted in any form or by any means, including photocopying, recording, or other electronic or mechanical methods, without the prior written permission of DSM.