



Preliminary Data Sheet of ER009734

TYPICAL PROPERTIES	TYPICAL VALUE	UNITS	STANDARD
MECHANICAL			
Tensile Modulus, 5 mm/min	17000	MPa	ASTM D 638
Tensile Stress, brk, 5 mm/min	100	MPa	ASTM D 638
Tensile Strain, brk, 5 mm/min	1.2	%	ASTM D 638
Flexural Stress, brk, 1.3 mm/min	120	MPa	ASTM D 790
Flexural Modulus, brk 1.3 mm/min	16500	MPa	ASTM D 790
Izod Impact, notched, 23°C	35	J/m	ASTM D 256
Izod Impact, unnotched, 23°C	80	J/m	ASTM D 4812
Izod Impact, notched, 23°C	3	kJ/m ²	ISO 180/1A
Izod Impact, unnotched, 23°C	7	kJ/m ²	ISO 180/1U
THERMAL			
HDT, 0.45 MPa, 3.2 mm	279	°C	ASTM D 648
HDT, 1.82 MPa, 3.2 mm	255	°C	ASTM D 648
Thermal Conductivity (in plane)	11	W/mk	ASTM E1461-07
Thermal Conductivity (through plane)	3	W/mk	ASTM E1461-07
CTE, -40°C to 40°C, flow	8E-06	1/°C	ASTM E 831
CTE, -40°C to 40°C, x-flow	2.7E-05	1/°C	ASTM E 831
PHYSICAL			
Density	1.65	g/cm ³	ISO 1183
Mold shrinkage, flow, 24h	0.1-0.2	%	ISO 294
Mold shrinkage, x-flow, 24h	0.1-0.3	%	ISO 294
Water absorption 23°C, 24h	0.01	%	ISO 62-1
ELECTRICAL			
Surface Resistivity	>1.0E+04	Ohm	ASTM D 257



Injection Molding Guidelines

Parameter Title	Range		Units
	Minimum	Maximum	
Melt Temperature	320	345	°C
Nozzle	325	345	°C
Front	325	345	°C
Middle	320	345	°C
Rear	320	345	°C
Mold Temperature	150	180	°C
Drying Temperature	120	140	°C
Drying Time (average)	3	4	h
Back Pressure	0.3	0.8	MPa
Screw Speed	60	100	rpm

1) Typical values only. Variations within normal tolerances are possible for various colours. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume rate are measured on injection moulded samples. All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.

3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

4) Own measurement according to UL.

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA **DISCLAIMER :** THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com>. AND ARE AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.