



Technical Data Sheet

TYPICAL PROPERTIES	WFC06I	UNIT	STANDARD
MECHANICAL			
Tensile Modulus, 5 mm/min	9355	MPa	ASTM D 638
Tensile Stress, break, 5 mm/min	125	MPa	ASTM D 638
Tensile Elongation, break, 5 mm/min	2.7	%	ASTM D 638
Flexural Modulus, 3.2 mm, 1.27 mm/min	8750	MPa	ASTM D 790
Flexural Stress, yield, 1.27 mm/min	200	MPa	ASTM D 790
IMPACT			
IZOD Impact, notched, -20 °C	115	J/m	ASTM D 256
IZOD Impact, notched, 23 °C	140	J/m	ASTM D 256
IZOD Impact, unnotched, 23 °C	965	J/m	ASTM D 256
Charpy Impact, notched, 23 °C	15	kJ/m ²	ISO 179
Charpy Impact, unnotched, 23 °C	65	kJ/m ²	ISO 179
THERMAL			
HDT, 0.45 MPa, 3.2 mm	200	°C	ASTM D 648
PHYSICAL			
MVR, 260 °C, 5 Kg	21	cm ³ /10 min	ASTM D 1238
Specific Gravity	1.5	g/cm ³	ASTM D 792
Mold Shrinkage, parallel	0.1~0.2	%	SABIC Method
Mold Shrinkage, perpendicular	0.1~0.2	%	SABIC Method
ELECTRICAL			
Dielectric Constant, 1.9GHz	3.5		SABIC Method
Dissipation Factor, 1.9GHz	0.008		SABIC Method
Laser			
Laser Transmission, 1.5mm	60	%	LPKF Method



Injection Molding Guidelines

Parameter Title	Range		Units
	Minimum	Maximum	
Drying Temperature	100	120	°C
Drying Time	3	4	h
Melt Temperature	260	290	°C
Nozzle Temperature	265	295	°C
Front – Zone 3 Temperature	260	290	°C
Middle – Zone 2 Temperature	260	290	°C
Rear – Zone 1 Temperature	250	280	°C
Mold Temperature	80	120	°C

1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured at least after 48 hours storage at 230C/50% relative humidity. All properties, except the melt volume rate are measured on injection molded samples. All samples are prepared according to ISO 294.

2) Only typical data for material selection purpose. Not to be used for part or tool design.

3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.

4) Own measurement according to UL.

PLEASE CONTACT YOUR LOCAL SALES OFFICE FOR AVAILABILITY IN YOUR AREA
 DISCLAIMER : THE MATERIALS, PRODUCTS AND SERVICES OF SABIC INNOVATIVE PLASTICS HOLDING BV, ITS SUBSIDIARIES AND AFFILIATES ("SELLER"), ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH CAN BE FOUND AT <http://www.sabic-ip.com>. AND ARE AVAILABLE UPON REQUEST.

ALTHOUGH ANY INFORMATION OR RECOMMENDATION CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SELLER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SELLER'S PRODUCTS, SERVICES OR RECOMMENDATIONS. EXCEPT AS PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user is responsible for making its own determination as to the suitability of Seller's products, services or recommendations for the user's particular use through appropriate end-use testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. No statement by Seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of such product, service or design in a manner that infringes any patent or other intellectual property right.