

Chemlon® 113 GH

Teknor Apex公司 - 聚酰胺66

2022年5月19日

一般信息

产品说明						
Chemlon® 113 GH is a 13% glass fiber reinforced, heat stabilized polyamide 66 (PA 66) designed for injection molding. This high tensile strength material has a wide processing window, provides a good surface appearance, and is available globally.						
总览						
材料状态	• 已商用：当前有效					
供货地区	• 北美洲 • 非洲和中东	• 拉丁美洲 • 欧洲	• 亚太地区			
添加剂	• 热稳定剂					
特性	• 高拉伸强度 • 良好的加工性能	• 热稳定性，良好 • 优良外观				
RoHS 合规性	• 联系制造商					
汽车要求	• CHRYSLER MS-DB-41 CPN2239 Color: BK001 黑色 ¹ • CHRYSLER MS-DB-41 CPN3794 Color: 无匹配颜色 ¹ • CHRYSLER MS-DB-41 CPN4061 Color: 100%颜色匹配 ¹	• FORD ESA-M4D349-A ¹ • GM GMP.PA66.020 Color: Black ¹ • GM GMP.PA66.020 Color: Natural ¹	• GM GMW3038P-PA66-GF15H Color: Black ¹			
形式	• 粒子					
加工方法	• 注射成型					

ASTM & ISO 属性²

物理性能	干燥	调节后的	单位制	测试方法
密度	1.22	--	g/cm ³	ISO 1183
收缩率 - 流动	0.40 到 0.70	--	%	ISO 294-4
机械性能	干燥	调节后的	单位制	测试方法
拉伸模量	7300	4160	MPa	ISO 527-1
拉伸应力	119	76.5	MPa	ISO 527-2
拉伸应变 (断裂)	2.2	16	%	ISO 527-2
弯曲模量	4650	3410	MPa	ISO 178
弯曲应力	170	94.4	MPa	ISO 178
冲击性能	干燥	调节后的	单位制	测试方法
简支梁缺口冲击强度	2.8	3.3	kJ/m ²	ISO 179
简支梁无缺口冲击强度	27	40	kJ/m ²	ISO 179
悬臂梁缺口冲击强度	> 3.0	> 3.3	kJ/m ²	ISO 180
热性能	干燥	调节后的	单位制	测试方法
载荷下热变形温度 (0.45 MPa, 未退火)	249	--	°C	ISO 75-2/B
载荷下热变形温度 (1.8 MPa, 未退火)	215	--	°C	ISO 75-2/A
熔融温度	257	--	°C	
电气性能	干燥	调节后的	单位制	测试方法
体积电阻率	1.0E+15	--	ohms·cm	ASTM D257
介电强度 (3.00 mm)	18	--	kV/mm	ASTM D149
相比耐漏电起痕指数(CTI)	600	--	V	UL 746A
可燃性	干燥	调节后的	单位制	测试方法
UL 阻燃等级 (0.8 mm)	HB	--		UL 94
极限氧指数	25	--	%	ASTM D2863

Revision Date: 2020/7/31

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

Chemlon® 113 GH
Teknor Apex公司 - 聚酰胺66

法律声明

干燥	The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.
----	--

加工信息

注射	干燥 单位制
干燥温度	80 °C
建议的最大水分含量	0.17 %
加工（熔体）温度	265 到 293 °C
模具温度	77 到 88 °C

注射说明

Maximum peak injection pressure should not exceed 80% of the machine's maximum pressure capability. Start with a holding pressure that is half the peak injection pressure. Perform a rheology curve in order to determine appropriate injection rate.

备注

- ¹ Automotive site approvals apply for US manufactured compound only
- ² 一般属性：这些不能被视为规格。

Teknor Apex Company Corporate Headquarters	Teknor Apex B.V.	Teknor Apex (Suzhou) Advanced Polymer Compounds Co. Pte. Ltd.	Teknor Apex Asia Pacific PTE. LTD.
In U.S. for Vinyls, TPEs, Colorants, Engineered Thermoplastics (Chem Polymer) 505 Central Avenue Pawtucket, Rhode Island 02861 U.S.	Mijnweg 1, 6167 AC Geleen, Netherlands	No. 78 Ping Sheng Road Suzhou Industrial Park Jiangsu, China 215126	41 Shipyard Road Singapore 628134
Phone: 401-725-8000 Fax: 401-725-8095 Toll Free (U.S. only) 800-556-3864	Phone: +31 46 7020 950 Fax: +31 46 7020 990	Phone: (86) 512-6287-1550 Fax: (86) 512-6288-8371	Phone: (65) 6265-2544 Fax: (65) 6265-1821
www.teknorapex.com info@teknorapex.com	www.teknorapex.com tpe@teknorapex.com	www.teknorapex.com infotaap@teknorapex.com	www.teknorapex.com infotaap@teknorapex.com