

Monprene® CP-18172

Thermoplastic Elastomer

Teknor Apex Company

PROSPECTOR®

www.ulprospector.com

Technical Data

Product Description

Monprene® CP-18172 is a Thermoplastic Elastomer (TPE) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for extrusion or injection molding. Primary attribute of Monprene® CP-18172: RoHS Compliant.

Typical applications include:

- Handles
- Business/Office Goods
- Caps/Lids/Closures
- Consumer Goods
- Engineering/Industrial Parts

General

Material Status	• Private		
Literature ¹	• Technical Datasheet		
Search for UL Yellow Card	• Teknor Apex Company • Monprene®		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Uses	• Closures • Consumer Applications • Gaskets • Handles	• Kitchenware • Medical/Healthcare Applications • Packaging • Safety Equipment	• Sporting Goods • Toothbrush Handles • Tubing • Writing Instruments
RoHS Compliance	• RoHS Compliant		
Appearance	• Clear/Transparent		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Physical

	Nominal Value Unit	Test Method
Density / Specific Gravity	0.888 g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	12 g/10 min	ASTM D1238

Elastomers

	Nominal Value Unit	Test Method
Tensile Stress (300% Strain)	3.45 MPa	ASTM D412
Tensile Strength (Break)	6.89 MPa	ASTM D412
Tensile Elongation (Break)	500 %	ASTM D412
Compression Set (23°C, 22 hr)	22 %	ASTM D395B

Hardness

	Nominal Value Unit	Test Method
Durometer Hardness (Shore A)	70	ASTM D2240

Injection

	Nominal Value Unit
Rear Temperature	182 to 232 °C
Middle Temperature	188 to 238 °C
Front Temperature	193 to 243 °C
Nozzle Temperature	199 to 249 °C
Processing (Melt) Temp	199 to 249 °C
Mold Temperature	35 to 49 °C
Injection Pressure	1.38 to 5.52 MPa
Injection Rate	Fast
Back Pressure	0.172 to 0.689 MPa
Screw Speed	50 to 100 rpm
Cushion	3.81 to 25.4 mm

Injection Notes

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).



Monprene® CP-18172

Thermoplastic Elastomer

Teknor Apex Company

PROSPECTOR®

www.ulprospector.com

Extrusion	Nominal Value Unit
Cylinder Zone 1 Temp.	182 to 232 °C
Cylinder Zone 2 Temp.	188 to 238 °C
Cylinder Zone 3 Temp.	193 to 243 °C
Cylinder Zone 5 Temp.	199 to 249 °C
Die Temperature	199 to 249 °C

Extrusion Notes

Screw Speed: 30 to 100 rpm

Notes

¹ These links provide you with access to supplier literature. We work hard to keep them up to date; however you may find the most current literature from the supplier.

² Typical properties: these are not to be construed as specifications.



Monprene® CP-18172

Thermoplastic Elastomer

Teknor Apex Company

PROSPECTOR®

www.ulprospector.com

Where to Buy

Supplier

Teknor Apex Company

Pawtucket, Pawtucket USA

Telephone: 800-556-3864

Web: <http://www.teknorapex.com/>

Distributor

Please contact the supplier to find a distributor for Monprene® CP-18172

